Doping Control of Magnetic Anisotropy for Stable Antiskyrmion Formation in Schreibersite (Fe,Ni)₃P with S_4 symmetry

Kosuke Karube,* Licong Peng, Jan Masell, Mamoun Hemmida, Hans-Albrecht Krug von Nidda, István Kézsmárki, Xiuzhen Yu, Yoshinori Tokura, and Yasujiro Taguchi*

Magnetic skyrmions, vortex-like topological spin textures, have attracted much interest in a wide range of research fields from fundamental physics to spintronics applications. Recently, growing attention is also paid to antiskyrmions emerging with opposite topological charge in non-centrosymmetric magnets with D_{2d} or S_4 symmetry. In these magnets, complex interplay among anisotropic Dzyaloshinskii-Moriya interaction, uniaxial magnetic anisotropy, and magnetic dipolar interactions generates various magnetic textures. However, the precise role of these magnetic interactions in stabilizing antiskyrmions remains to be elucidated. In this work, the uniaxial magnetic anisotropy of schreibersite (Fe,Ni)₃P with S₄ symmetry is controlled by doping and its impact on the stability of antiskyrmions is investigated. The authors' magnetometry study, supported by ferromagnetic resonance spectroscopy, shows that the variation of the Ni content and slight doping with 4d transition metals considerably change the magnetic anisotropy. In particular, doping with Pd induces easy-axis anisotropy, giving rise to formation of antiskyrmions, while a temperature-induced spin reorientation is observed in an Rh-doped compound. In combination with Lorentz transmission electron microscopy and micromagnetic simulations, the stability of antiskyrmion as functions of uniaxial anisotropy and demagnetization energy is quantitatively analyzed, and demonstrated that subtle balance between them is necessary to stabilize the antiskyrmions.

1. Introduction

Vortex-like spin swirling objects, termed magnetic skyrmions and characterized by an integer topological winding number N_{sk} ,

K. Karube, L. Peng, J. Masell, X. Yu, Y. Tokura, Y. Taguchi RIKEN Center for Emergent Matter Science (CEMS) Wako 351-0198, Japan E-mail: kosuke.karube@riken.jp; y-taguchi@riken.jp J. Masell Institute of Theoretical Solid State Physics Karlsruhe Institute of Technology (KIT) Karlsruhe 76049, Germany

The ORCID identification number(s) for the author(s) of this article can be found under https://doi.org/10.1002/adma.202108770.

have been extensively studied in the last decade, both in the fields of fundamental science and applications to spintronics devices.^[1,2] One of the well-known mechanisms of skyrmion formation is the competition between ferromagnetic exchange interaction and the Dzyaloshinskii-Moriya interaction (DMI) arising from the lack of inversion symmetry. Skyrmions with helical (Bloch type) and cycloidal (Néel type) spin configurations have been observed in non-centrosymmetric magnets with chiral (*T* or *O* class) and polar (C_{ny} class) structures, respectively.^[3–9] Recently, a new topological spin texture, the antiskyrmion, with opposite sign of $N_{\rm sk}$ for the same polarity has attracted much attention. The antiskyrmion consists of both Bloch and Néel walls with the opposite helicities along two orthogonal axes, and its formation is attributed to the anisotropic DMI present in non-centrosymmetric tetragonal crystals belonging to the D_{2d} or S₄ symmetry group both containing fourfold rotoinversion (4).^[10,11] In real materials, antiskyrmions were first found in Heusler compounds with D_{2d} symmetry, Mn_{1.4}PtSn and Mn_{1.4}Pt_{0.9}Pd_{0.1}Sn.^[12,13]

More recently, the formation of antiskyrmions was also found in $Fe_{1.9}Ni_{0.9}Pd_{0.2}P$ [Pd-doped (Fe,Ni)₃P] with S_4 symmetry^[14] and Fe/Gd-based multilayers.^[15] Lorentz transmission electron microscopy (LTEM) observation for thin plates of these

M. Hemmida, H.-A. Krug von Nidda, I. Kézsmárki Experimental Physics V University of Augsburg Augsburg 86135, Germany Y. Tokura Department of Applied Physics University of Tokyo Bunkyo-ku 113-8656, Japan Y. Tokura Tokyo College University of Tokyo Bunkyo-ku 113-8656, Japan

Table 1. Lattice constants (*a*, *c*) at room temperature, magnetic transition temperature (T_c), saturation magnetization (M_s), and uniaxial anisotropy constant (K_u) at 300 and 2 K for (Fe,Ni)₃P and doped with 4d transition metals.

Composition	a [Å]	<i>c</i> [Å]	<i>T</i> _c [K]	<i>M</i> _s (300 K) [kA m ⁻¹]	<i>M</i> _s (2 K) [kA m ⁻¹]	<i>K</i> _u (300 K) [kJ m ⁻³]	<i>K</i> _u (2 K) [kJ m ⁻³]
Fe ₃ P	9.1018(8)	4.4587(4)	681	1080	1160	-647	-848
(Fe _{0.82} Ni _{0.18}) ₃ P	9.0713(4)	4.4627(2)	557	801	925	-98.4	-205
(Fe _{0.63} Ni _{0.37}) ₃ P	9.0425(5)	4.4607(3)	412	518	743	-6.73	-38.8
(Fe _{0.53} Ni _{0.47}) ₃ P	9.0266(5)	4.4561(3)	334	306	632	-4.06	-44.6
(Fe _{0.34} Ni _{0.66}) ₃ P	9.0006(5)	4.4429(3)	152	-	381	-	-62.4
(Fe _{0.59} Ni _{0.32} Ru _{0.09}) ₃ P	9.0934(6)	4.4907(3)	337	363	693	-5.65	-53.2
(Fe _{0.60} Ni _{0.32} Rh _{0.08}) ₃ P	9.0931(7)	4.4855(4)	394	503	731	1.89	-20.1
(Fe _{0.63} Ni _{0.33} Pd _{0.04}) ₃ P	9.0797(6)	4.4745(3)	399	511	750	22.2	51.3
$({\sf Fe}_{0.63}{\sf Ni}_{0.30}{\sf Pd}_{0.07})_{3}{\sf P}$	9.1122(7)	4.4865(4)	398	474	707	27.9	83.8
(Fe _{0.62} Ni _{0.29} Pd _{0.09}) ₃ P	9.1199(6)	4.4895(3)	392	451	704	33.5	114

 D_{2d} and S_4 magnets shows that the antiskyrmions are square shaped, and transform into bullet-shaped non-topological bubbles and elliptically deformed Bloch skyrmions, depending on magnetic fields, temperature, and lamella thickness.^[13,14,16] According to numerical simulations, magnetic dipolar interaction (demagnetization energy) plays a dominant role in the formation of square-shaped antiskyrmions;^[13,16,17] Néel walls (Bloch lines) at the corners of an antiskyrmion tend to shrink so as to reduce the magnetic volume charge.^[18] Magnetic force microscopy studies have shown that the size of antiskyrmions increases significantly as the crystal thickness is increased,^[14,19] and anisotropic fractal-like domains with $\overline{4}$ symmetry are induced near the surface of bulk crystals^[14,20] by the interplay between DMI, uniaxial magnetic anisotropy, and dipolar interactions to reduce the magnetic charge on the surface.^[21]

Despite these findings in the two families of antiskyrmionhosting magnets, the relation between the stability of antiskyrmions and magnetic interactions (DMI, magnetic anisotropy, and dipolar interaction) is still unclear due to the lack of experimental studies where the relative strength of magnetic interactions is tuned systematically. In this work, we succeeded in controlling the magnetic anisotropy of schreibersite (Fe,Ni)₃P with S_4 symmetry by chemical doping to observe the formation of stable antiskyrmions. First, we searched for the appropriate solid solution of Fe and Ni to reduce the easy-plane anisotropy. Next, using 4d transition metals with strong spin-orbit coupling, we further modified the magnetic anisotropy to easy-axis type, leading to the formation of stable antiskyrmions and skyrmions. We finally identified the stable region of antiskyrmions and skyrmions on the plane of uniaxial magnetic anisotropy and demagnetization energy, thereby demonstrating the subtle balance between them to give rise to the antiskyrmion spin texture.

2. Results and Discussions

2.1. Structural Properties

We synthesized bulk single crystals of schreibersite $(Fe_{1-x}Ni_x)_3P$ ($0 \le x \le 0.66$) and those doped with small amounts of 4d transition metals (Ru, Rh, and Pd) listed in **Table 1** by a self-flux method (see Note S1, Table S1, Supporting Information for details of sample preparation). Using powder X-ray diffraction, we confirmed that all the compounds crystalize in a non-centrosymmetric tetragonal structure with the space group of $I\overline{4}$ (No. 82, S_4^2) as shown in **Figure 1**a (see Note S2, Figures S1,S2, Supporting Information for details). The tetragonal lattice constants (*a*, *c*) obtained by Rietveld analysis are plotted in Figure 1b. The parameter *a* decreases linearly with increasing Ni concentration, while *c* is almost unchanged below x = 0.47, in good agreement with a previous study.^[22] When a small amount of Pd is substituted for Ni, both *a* and *c* increase linearly following Vegard's law. Similar increase in the lattice constants is also observed with Ru and Rh doping.

2.2. Magnetometry

To characterize bulk magnetic properties, magnetization (*M*) was measured under magnetic fields applied parallel to the [110] and [001] axes, being perpendicular and parallel to the $\overline{4}$ axis, respectively. For the magnetization measurements, single crystals were cut into a rectangular shape (Figure S3, Supporting Information) so that the demagnetization factors in the [110] and [001] directions were the same. By adopting this sample shape with the same demagnetization factors, the uniaxial magnetic anisotropy constant (K_{ul}) is directly obtained, without explicitly taking the demagnetization effect into account, from the difference between the Helmholtz magnetic free energy along the [110] and [001] axes,^[23]

$$K_{u} = \int_{0}^{M_{s}} \left[H_{[110]} \left(M \right) - H_{[001]} \left(M \right) \right] dM$$
(1)

where M_s is the saturation magnetization, and $H_i(M)$ represents the magnetic field along the *i*-axis. Therefore, K_u is equal to the area enclosed by the magnetization curves along the two directions. In the present case, the magnetization process along the easy axis is dominated by the displacement of domain walls, but the contribution of this process is excluded in Equation (1). The sign of K_u indicates the direction of the anisotropy; $K_u > 0$ for the easy-axis anisotropy while $K_u < 0$ for the easy-plane type.

The temperature dependence M(T) at 0.01 T and the magnetic field variation M(H) at 2 K in $(Fe_{1-x}Ni_x)_3P$ are presented



Figure 1. Structural properties of $(Fe_{1-x}Ni_x)_3P$. a) Crystal structure of M_3P (M: transition metal) with the non-centrosymmetric tetragonal space group of $I\overline{4}$. The structure viewed from the *c*-axis is shown at the bottom. Three crystallographically inequivalent M sites are denoted as M1 (red), M2 (green), and M3 (blue). b) Lattice constants *a* and *c* at room temperature obtained from powder X-ray diffraction and Rietveld analysis are plotted as a function of *x* of $(Fe_{1-x}Ni_x)_3P$ and γ of $(Fe_{0.63}Ni_{0.37-\gamma}Pd_y)_3P$. The data for $(Fe_{1-x}Ni_x)_3P$ from literature are also plotted with cross symbols.^[22] The data points of $(Fe_{0.62}Ni_{0.29}Pd_{0.09})_3P$ plotted with open symbols deviate from the linear fit due to the slightly lower Fe concentration.

in **Figure 2**. Fe₃P exhibits a ferromagnetic transition around 680 K and shows strong easy-plane anisotropy, as indicated by smaller *M* values and larger saturation field in the [001] axis than those in the [110] axis (Figure 2a,f). Partial substitution of Fe with Ni lowers the magnetic transition temperature T_c (Figure 2b–e) and decreases the saturation value of magnetization M_s (Figure 2g–j). Furthermore, the difference between the magnetization curves along the [110] and [001] axes becomes smaller as the Ni substitution proceeds, and is the smallest at the Ni concentration of 37%. M(T) of (Fe_{0.34}Ni_{0.66})₃P decreases below 40 K (Figure 2e) probably due to the spin glass behavior of the diluted Fe moments.

The magnetic parameters, T_c , M_s , and K_u , obtained from the magnetization measurements using Equation (1) are plotted in Figure 2k–m as a function of Ni concentration x. The monotonous decrease in T_c and M_s with increasing x is in accord with the previous report on polycrystalline samples.^[22] While there have been several studies on the magnetic properties of $(Fe_{1-x}M_x)_3P$ (M: Cr, Mn, Co, and Ni),^[22,24–26] magnetocrystalline anisotropy has been reported only for $(Fe_{1-x}Co_x)_3P$.^[27] As shown in Figure 2m, the large negative value of K_u for Fe₃P (–848 kJ m⁻³ at 2 K) determined in the present study coincides with the previous report.^[27] The absolute value of K_u is rapidly suppressed by Ni substitution, reaching a minimum at x = 0.37 (–39 kJ m⁻³ at 2 K). Nevertheless, the easy-plane anisotropy ($K_u < 0$) persists throughout the whole Ni concentration range in the present study of $(Fe_{1-x}Ni_x)_3P$.

Having thus established that the strong in-plane magnetic anisotropy (negative $K_{\rm u}$) in $({\rm Fe}_{1-x}{\rm Ni}_x)_3{\rm P}$ can be appreciably reduced around $x \approx 0.4$ while keeping high $T_{\rm c}$ above room temperature, next we aim to further control $K_{\rm u}$ and to reverse its sign via doping with 4d transition metals. **Figure 3** shows the effect of 4d transition-metal doping on the magnetic properties. In the Ru-doped compound, (Fe_{0.59}Ni_{0.32}Ru_{0.09})₃P (Figure 3a,f),

weak easy-plane anisotropy is observed in the whole temperature range below $T_c \approx 340$ K, as in the case of (Fe,Ni)₃P. On the other hand, the Rh-doped sample, (Fe_{0.60}Ni_{0.32}Rh_{0.08})₃P (Figure 3b,g), shows a complex temperature dependence. Below $T_c \approx 400$ K, the magnetization along the [110] axis increases gradually upon cooling, whereas that along the [001] axis is almost independent of temperature. The magnetization along the [110] axis saturates at 100 K, below which the magnetization along the [001] axis slightly decreases. This behavior is a typical indicator of spin reorientation from the *c*-axis to the *ab*-plane, which is often seen in uniaxial ferromagnets such as MnBi,^[28] Fe₃Sn₂,^[29,30] and Mn_{1.4}PtSn.^[31] The spin reorientation temperature in the Rh-doped compound is determined to be $T_{\rm SR} \approx 100$ K where the kink-like anomaly is observed. As for another dopant Pd, 4% doped (Fe_{0.63}Ni_{0.33}Pd_{0.04})₃P (Figure 3c,h) does not show spin reorientation and exhibits weak easy-axis anisotropy in the whole temperature range below $T_c \approx 400$ K. In Pd 7% doped (Fe_{0.63}Ni_{0.30}Pd_{0.07})₃P (Figure 3d,i) and 9% doped (Fe_{0.62}Ni_{0.29}Pd_{0.09})₃P (Figure 3e,j), the easy-axis anisotropy is more clearly seen than in the Pd 4% doped sample.

The values of M_s and K_u in the investigated compounds are plotted against temperature in Figure 3k,l. While the M_s values are similar for the different compositions, the sign and the absolute value of K_u considerably change with the 4d metal dopant species. In particular, easy-axis anisotropy ($K_u > 0$) is induced by small amount of Pd doping, and the value of K_u increases with decreasing temperature and increasing the Pd concentration. The temperature dependences of K_u and M_s in the Pd 7% and 9% doped compounds are found to obey the relation $K_u(T) \approx [M_s(T)]^{2.7}$ (Figure S4, Supporting Information). The power law with an exponent close to 3 agrees with the theoretical models for uniaxial anisotropy.^[32–34] For the Pd 7% compound that shows $M_s \approx 474$ kA m⁻¹ and $K_u \approx 28$ kJ m⁻³ at room temperature, the quality factor is estimated to be $Q \approx 0.2$, where Q is defined



Figure 2. Magnetic properties of $(Fe_{1-x}Ni_x)_3P$. Temperature (*T*) dependence of magnetization *M* under the magnetic field $\mu_0H = 0.01$ T for a) Fe₃P, b) $(Fe_{0.82}Ni_{0.18})_3P$, c) $(Fe_{0.63}Ni_{0.37})_3P$, d) $(Fe_{0.53}Ni_{0.47})_3P$, and e) $(Fe_{0.34}Ni_{0.66})_3P$. The data of field cooling (FC) and field warming after a zero-field cooling (ZFC) are denoted with solid and dotted lines, respectively. f–j) Magnetic field dependence of magnetization at 2 K for the same compositions as shown in the panels (a–e). Magnetizations for the [110] and [001] axes are shown by red and blue lines, respectively. The schematic figure of a rectangular bulk single crystal used for the measurements is shown at the top of panel (f). Ni concentration *x* dependence of k) ferromagnetic transition temperature T_c , l) saturation magnetization M_s , and m) uniaxial anisotropy constant K_u at 300 and 2 K obtained from the magnetization measurements. The value of M_s was determined as the magnetization at $\mu_0H = 3$ T for Fe₃P, 2 T for x = 0.18, and 1 T for $x \ge 0.37$. For the conversion of M_s and K_u to unit volume, the lattice constants obtained by powder X-ray diffraction at room temperature were used. T_c and M_s of polycrystalline (Fe_{1-x}Ni_x)₃P in the literature are indicated by cross symbols.^[27] M_s and K_u of Fe₃P at 300 and 5 K in the literature are shown with open symbols.^[27]

as $Q = K_u / (\mu_0 M_s^2 / 2)$, the ratio of the uniaxial anisotropy constant to the maximum of demagnetization energy. These K_{μ} and Q values are small as compared with those of the industriallyimportant commercial permanent magnets, such as (Sr,Ba) $Fe_{12}O_{19}$, Nd₂Fe₁₄B, SmCo₅,^[35] and the recently reported Heusler compound Mn_{1.4}PtSn ($K_u \approx 171 \text{ kJ m}^{-3}$, $Q \approx 1.7 \text{ at room tempera$ ture).^[36] The values of K_u for the Rh-doped compound are inbetween those for the Ru- and Pd-doped ones, and change from very small positive values at room temperature to negative values at low temperatures, leading to the temperature-induced spin reorientation. The significant change in the magnetic anisotropy from easy-plane to easy-axis with the Pd doping indicates the importance of enhanced spin-orbit coupling in the 4d element. The systematic variation in the magnetic anisotropy with change in the dopants Ru, Rh, and Pd is probably dominated by band filling of 4d orbitals, or position of the Fermi level.

While the systematic change of K_u with composition and temperature was identified by the magnetometry study using

Equation (1), we performed ferromagnetic resonance (FMR) spectroscopy experiments on the Pd 7% compound to determine K_u by another method, and thus further validate our magnetometry-based approach for the quantification of anisotropy.

2.3. Ferromagnetic Resonance Spectroscopy

We carried out FMR spectroscopy measurements at 9.4 GHz on a cylindrical disk prepared from a Pd 7% crystal and shown in the inset of **Figure 4**b. Figure 4a displays representative fieldswept FMR spectra recorded at room temperature for various orientations of the magnetic field applied in the plane of the disk, which contains both the [110] and [001] axes. The maxima of the microwave absorption curves correspond to the FMR field, $H_{\rm res}$, whose angular dependence is displayed in Figure 4b for a full rotation of the field in the plane of the disk. The minimum of $H_{\rm res}$ is observed for magnetic field along the [001]



Figure 3. Magnetic properties of 4d-metal doped compounds. Temperature dependence of magnetization under the magnetic field of $\mu_0 H = 0.01$ T for a) (Fe_{0.59}Ni_{0.32}Ru_{0.09})₃P, b) (Fe_{0.60}Ni_{0.32}Rh_{0.08})₃P, c) (Fe_{0.63}Ni_{0.33}Pd_{0.04})₃P, d) (Fe_{0.63}Ni_{0.30}Pd_{0.07})₃P (equivalent to the notation Fe_{1.9}Ni_{0.9}Pd_{0.2}P as adopted in our earlier work^[14]), and e) (Fe_{0.62}Ni_{0.29}Pd_{0.09})₃P. f–j) Magnetic field dependence of magnetization at 2 K for the same compositions as shown in the panels (a–e). The magnetization data for Pd 9% are reproduced with permission from our earlier work.^[14] (Copyright 2021, Springer Nature). The schematic figure of a rectangular bulk single crystal used for the measurements is shown at the top of panel (f). Temperature dependence of k) M_s and l) K_u obtained from the magnetization measurements for the various compositions. The value of M_s was determined as the magnetization at 1 T for all the compounds. The values of K_u in (Fe_{0.63}Ni_{0.39}Pd_{0.07})₃P obtained from the FMR measurement are also plotted with yellow star symbols.

axis, while the maximum is reached for field parallel to the [110] axis, clearly demonstrating the easy-axis nature of the anisotropy with the [001] direction being the easy axis. Due to the cylindrical shape of the sample, the demagnetization factor is unchanged upon the field rotation, hence the angular dependence of H_{res} is solely governed by K_{u} . Similar $H_{\text{res}}(\theta)$ curves were recorded at 250, 350, and 380 K. The K_{u} values obtained by fitting these curves, as described in the Experimental Section and in refs. [^{37–39}] are plotted in Figure 31. These values are in excellent agreement with those obtained from the analysis of the magnetization, supporting the fully quantitative determination of K_{u} in the present work.

2.4. Magnetic Textures Observed by Lorentz Transmission Electron Microscopy

In order to observe magnetic structures in real space, LTEM measurements were carried out on (001) thin plates. We pre-

sent the magnetic induction fields as deduced by transport-ofintensity equation (TIE) analyses for the compounds with Pd 7% (thickness $t \approx 130$ nm), Pd 4% ($t \approx 140$ nm), and Rh 8% ($t \approx$ 180 nm) in **Figure 5**. The stripe pattern with a few hundred nm periods observed for all the compounds at room temperature and zero magnetic field (Figure 5a,d,g) corresponds to anisotropic helices with opposite helicities propagating along the [110] and [$\overline{110}$] axes.

In the Pd 7% sample, square antiskyrmions appear uniformly over the plate under a magnetic field perpendicular to the specimen (Figure 5b). Note that high-density antiskyrmions are observed only after the sample plate is tilted under a magnetic field to initially create non-topological bubbles, and tilted back to the original perpendicular position as detailed in the caption for Figure 5.^[14] Similar antiskyrmion lattices are observed at low temperatures down to 100 K (Figure 5c).

In the Pd 4% sample, square antiskyrmions and elliptically deformed skyrmions coexist under a magnetic field (Figure 5e). This coexistence state is also observed for $t \approx 170$, 190, and



Figure 4. Ferromagnetic resonance (FMR) spectroscopy on $(Fe_{0.63}Ni_{0.30}Pd_{0.07})_3P$ at 300 K. a) FMR spectra, representing the absorbed power P_{abs} as a function of the magnetic field strength, μ_0H , at a constant microwave frequency 9.4 GHz, displayed at selected θ angles of the magnetic field. The vertical bars, marking the resonance field positions, are guides to the eyes for tracing the angular periodicity of the spectra. b) Dependence of the resonance field at room temperature on the orientation of the magnetic field, $H_{res}(\theta)$, upon its rotation in the plane spanned by the [001] and [110] axes. The angle θ is measured from the [001] axis as indicated in the inset, which depicts the single crystal under investigation prepared as a thin cylindrical disk. The solid black line shows a fit by uniaxial magnetocrystalline anisotropy.^[37–39] as described in the text.

220 nm, but a homogeneous antiskyrmion lattice is not formed. At the thickness of $t \approx 80$ nm, only elliptic skyrmions are observed. The (co)existence of skyrmions in spite of the anisotropic DMI indicates that the dipolar interaction is dominant over the DMI in this system.

In the Rh 8% sample, while dense elliptic skyrmions with mixed helicities are stabilized under a magnetic field (Figure 5h), no antiskyrmions are observed at any field for any sample thickness from 70 to 240 nm. As the temperature is lowered in zero field, the stripe pattern changes to large (approximately several micrometers) domains with in-plane magnetizations (Figure 5j), which is consistent with the behavior of spin reorientation in the bulk magnetization measurement (Figure 3b). The in-plane domains are arranged in such a way that the magnetic flux is closed as indicated with white arrows. The transition from the anisotropic helices to the in-plane closure domains starts at higher temperatures for smaller thickness, for example, 200 K for $t \approx 70$ nm, 143 K for $t \approx 110$ and 150 nm, and 130 K for $t \approx 180$ nm. Furthermore, this transformation is accompanied by a coexistence region and a large thermal hysteresis; the stripe patterns remain partially at low temperatures, but once the change into the in-plane domains is complete, they hardly recover in a subsequent heating process (Figure S5, Supporting Information).

In Figure 5f,i, enlarged views of an elliptic skyrmion are presented. The elliptic deformation is due to the cooperative interplay between the dipolar interaction and the anisotropic DMI inherent to the crystal structure with D_{2d} or S_4 symmetry,^[13,14,16] and hence distinct from elliptic skyrmions induced by artificial

anisotropy.^[40,41] From the observed ellipticity, the magnitude of DMI is roughly estimated to be ≈26% of the demagnetization energy.^[13] In addition, the variation of the DMI with composition is negligible since the ellipticity of the skyrmion is comparable for the Pd 4% and Rh 8% compounds. Although the change in the DMI for these compounds investigated in this work is small, it might vary significantly in a wider compositional range, similarly to the Co/Pt bilayers where the interfacial DMI depends on the band filling of 5d orbitals.^[42] To determine the anisotropic DMI more quantitatively and understand its compositional dependence comprehensively, further studies (e.g., Brillouin light scattering,[43] spin-wave spectroscopy[44]) are necessary. Therefore, while the anisotropic DMI in this system is indeed important, we focus hereafter on the effects of larger and composition/temperature-dependent demagnetization energy and magnetic anisotropy on the formation of the topological spin textures.

2.5. Stability of Antiskyrmions Governed by Demagnetization Energy and Uniaxial Anisotropy

To understand the effect of the thickness-dependent dipolar interactions quantitatively, we estimate demagnetization energy E_d for the thin plates using the following theoretical equation for a helical stripe (Bloch wall type) with a period of λ and a film thickness of $t_{\lambda}^{[19,45]}$

$$E_{\rm d} = \frac{\mu_0 M_{\rm s}^2}{2} f\left(\frac{2\pi t}{\lambda}\right) \tag{2}$$



Figure 5. Magnetic structures observed by LTEM. a–j) Color mapping of in-plane magnetic induction fields deduced by transport-of-intensity equation (TIE) analyses of over- and under-focus LTEM images.^[50] The color-coded wheel and the schematic figure of the experimental configuration (crystal axes of the thin plate and the external field) at the bottom right side are common for all the panels. The images of antiskyrmions and skyrmions (panels (b,c,e,h)) were obtained after tilting the plate under the external field and then back to the original position, as described in the following, where the tilt angles around the [110] and [110] axes are denoted as α and β , respectively. Field images for (Fe_{0.63}Ni_{0.30}Pd_{0.07})₃P with thickness $t \approx 130$ nm at (a) 295 K and 0 mT, (b) 295 K and 350 mT [process: 0 mT ($\alpha \approx 0^{\circ}$) $\rightarrow 350$ mT ($\alpha \approx 12^{\circ}$) $\rightarrow 350$ mT ($\alpha \approx 0^{\circ}$)], and (c) 100 K and 650 mT [process: ZFC \rightarrow 100 K and 0 mT ($\alpha \approx 0^{\circ}$) $\rightarrow 550$ mT ($\alpha \approx 12^{\circ}$) $\rightarrow 550$ mT ($\alpha \approx 0^{\circ}$) $\rightarrow 550$ mT ($\alpha \approx 0^{\circ}$) $\rightarrow 550$ mT ($\alpha \approx 0^{\circ}$) $\rightarrow 385$ mT ($\alpha \approx 2^{\circ}$)]. Field images for (Fe_{0.63}Ni_{0.33}Pd_{0.04})₃P with $t \approx 140$ nm at (d) 295 K and 0 mT, and (e,f) 295 K and 385 mT [process: 0 mT ($\alpha \approx 0^{\circ}$) $\rightarrow 385$ mT ($\alpha \approx 2.4^{\circ}$, $\beta \approx 1^{\circ}$) $\rightarrow 385$ mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$)]. Field images for (Fe_{0.60}Ni_{0.33}Pd_{0.04})₃P with $t \approx 140$ nm at (g) 295 K and 0 mT, (h,i) 295 K and 450 mT [process: 0 mT ($\alpha \approx 0^{\circ}$) $\rightarrow 450$ mT ($\alpha \approx 0^{\circ}$)]. Field images for (Fe_{0.60}Ni_{0.32}Rh_{0.03})₃P with $t \approx 180$ nm at (g) 295 K and 0 mT, (h,i) 295 K and 450 mT [process: 0 mT ($\alpha \approx 0^{\circ}$) $\rightarrow 450$ mT ($\alpha \approx 0^{\circ}$)]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]]. Field images for mT ($\alpha \approx 0^{\circ}$, $\beta \approx 0^{\circ}$]]

where the function f(x) is defined as $f(x) = (1 - e^{-x})/x$. For small x (i.e., $t \ll \lambda$), f(x) is simplified as $f(x) \approx 1 - x/2$, while $f(x) \approx 1/x$ for large x (i.e., $t \gg \lambda$). **Figure 6**a shows $\lambda(t)$ of the anisotropic helices at room temperature and zero field for the composition with Pd 7%, Pd 4%, and Rh 8%. The thickness dependence is well described by the Kittel's law ($\lambda \propto t^{1/2}$),^[46] which is attributed to the competition between demagnetization energy and domain wall energy. The calculated E_d by using Equation (2) at room temperature for each compound is plotted against t in Figure 6b, which increases monotonically with decreasing thickness.

Finally, we map out the magnetic objects observed by LTEM onto the plane of K_u and E_d in Figure 6c. Here, anisotropic helices and in-plane domains at zero field, and antiskyrmions/ skyrmions under magnetic fields are plotted all together. The K_u – E_d phase diagram indicates that antiskyrmions are stabilized when K_u is positive, sufficiently large and comparable to E_d . On the other hand, when K_u is very small as compared

to E_d , as in the cases of Rh doping, or Pd doping with small thickness, elliptic skyrmions become more dominant. This result proves that the strong dipolar interaction destabilizes the antiskyrmions with magnetic volume charge, and favors the Bloch skyrmions without it. Therefore, uniaxial anisotropy and dipolar interaction are both important ingredients for stabilizing antiskyrmions in S_4 magnets with anisotropic DMI (and probably D_{2d} magnets as well). The significant role of uniaxial anisotropy and dipolar interaction for stabilizing antiskyrmions has been also demonstrated in multilayers.^[15]

The phase diagram in Figure 6c also describes the temperature-induced change from the anisotropic helices to the in-plane domains when the sign of K_u changes to negative in the case of the Rh 8% doping (although initially formed anisotropic helices at room temperature with $K_u > 0$ can survive to the region of $K_u < 0$ as a metastable state). The phase boundary between the helices and the in-plane domains shows a positive slope, indicating that the dipolar interaction also contributes to the spin reorientation.



Figure 6. Demagnetization energy and magnetic phase diagram. Thickness (*t*) dependence of a) magnetic periodicity λ of the anisotropic helix and b) demagnetization energy E_d at room temperature for (Fe_{0.63}Ni_{0.30}Pd_{0.07})₃P, (Fe_{0.63}Ni_{0.33}Pd_{0.04})₃P, and (Fe_{0.60}Ni_{0.32}Rh_{0.08})₃P. c) Magnetic phase diagram observed by LTEM on the plane of uniaxial anisotropy constant K_u and E_d . All the spin textures are plotted together, which include anisotropic helix and in-plane domains at zero field, and antiskyrmions and skyrmions under fields, for the Pd 7%, Pd 4%, and Rh 8% compounds with various thicknesses shown in panel (b). Low-temperature data for Pd 7% (*t* = 130 nm) and Rh 8% (*t* ≤ 180 nm) are also included. The data points for Pd 7% are reproduced in part from our earlier work.^[14] (Copyright 2021, Springer Nature).

The easy-plane anisotropy may also give rise to more interesting in-plane topological magnetism such as bimeron.^[47,48]

observations and the argument that DMI-stabilized antiskyrmions benefit from the larger volume fraction.

2.6. Micromagnetic Simulations

The experimental observation of the antiskyrmions stabilized by uniaxial anisotropy is in qualitative agreement with our micromagnetic simulations, presented in Figure 7. In Figure 7a, we show simulation results of magnetic textures at various K_{u} and external magnetic fields with a constant dipolar energy density of $E_d = 66 \text{ kJ m}^{-3}$ (note that the horizontal axis is different from that in Figure 6c). We start from an initially triangular antiskyrmion lattice and relax it at finite temperature. As a result, we obtain a field-polarized ferromagnetic state at large magnetic fields $\mu_0 H \ge 500$ mT, in-plane states at low anisotropy $K_{\rm u} \leq 30$ kJ m⁻³, and antiskyrmions at large anisotropies $K_{\rm u} \ge 70 \text{ kJ m}^{-3} \approx E_{\rm d}$ of the order of the dipolar energy density $E_{\rm d}$ and average external magnetic fields $\mu_0 H \leq 375$ mT. This antiskyrmion phase pocket is surrounded by a belt of dipolar stabilized skyrmions, including a crossover regime where skyrmions and antiskyrmions coexist. A particularly instructive example is displayed in the panel for $\mu_0 H = 300$ mT and $K_{\mu} =$ 80 kJ m⁻³ (enlarged view is shown in Figure 7c), which contains the characteristically distorted anti-/skyrmions: two squareshaped antiskyrmions in the lower row and in the upper row two elliptical skyrmions with opposite handedness and consequently, perpendicular elongation axes. Moreover, we checked that for thicker films the onset of the antiskyrmion phase shifts to lower anisotropies, in agreement with both our experimental

3. Conclusion

We have systematically studied the magnetic properties of schreibersite (Fe,Ni)₃P with S₄ symmetry by performing magnetometry, FMR spectroscopy, LTEM, and micromagnetic simulations, demonstrating that the magnetic anisotropy can be finely controlled by the composition to stabilize antiskyrmions. The strong easy-plane anisotropy of Fe₃P is rapidly suppressed by partial Ni substitution, and when additionally doped with a small amount of Pd, the magnetic anisotropy switches to an easy-axis type, leading to the formation of antiskyrmions. The Rh-doped compound exhibits a temperature-induced spin reorientation transition, which is directly observed by LTEM. The phase diagram regarding the magnetic textures clearly shows stable regions of antiskyrmions and elliptic skyrmions on the plane of the uniaxial anisotropy and the demagnetization energy. These findings unveil that easy-axis type uniaxial magnetic anisotropy and dipolar interaction with appropriate balance are both necessary to stabilize antiskyrmions, and will help to design new antiskyrmion systems toward applications in spintronics.

4. Experimental Section

Sample Preparation: Bulk single crystals of M_3P (M: Fe, Ni, Ru, Rh, and Pd) were synthesized by a self-flux method from the initial molar ratio



Figure 7. Thickness-averaged magnetization as obtained from 3D micromagnetic simulations for a 100 nm thick film. a) Simulated magnetic textures on the plane of uniaxial anisotropy energy K_u and external magnetic field $\mu_0 H$. The color encodes the orientation of the magnetization with white (black) indicating the +z (-z) component. The color of the frame of every panel encodes the total skyrmion number from +4 (blue, four skyrmions) to -4 (red, four antiskyrmions). The dipolar energy density in the simulations is $E_d = 66$ kJ m⁻³. Enlarged views of the magnetic textures at $\mu_0 H = 300$ mT and b) $K_u = 140$, c) 80, and d) 40 kJ m⁻³, where the skyrmion number for each magnetic object is also indicated (+1 for skyrmion, -1 for antiskyrmion).

of M:P \approx 3.5:1 (Note S1, Table S1, Supporting Information). Chemical compositions of the obtained crystals were determined by the energy dispersive X-ray analysis (Table S1, Supporting Information). Lattice constants of M₃P with the non-centrosymmetric tetragonal structure were determined by powder X-ray diffraction and Rietveld analysis (Note S2, Figures S1,S2, Supporting Information).

Magnetization Measurement: For magnetization measurements, single crystals were cut into a 1-mm-scale rectangle with flat (110) and (001) surfaces and approximately the same length along the [110] and [001] axes (Figure S3, Supporting Information). Magnetization measurements were carried out using a superconducting quantum interference device magnetometer (MPMS3, Quantum Design) equipped with an oven option.

FMR Measurement: Angular dependent FMR experiments were performed for the temperature range 250 K $\leq T \leq$ 380 K, using a Bruker ELEXSYS E500 CW X-band (9.4 GHz) spectrometer. The sample of (Fe_{0.63}Ni_{0.30}Pd_{0.07})₃P was in a continuous nitrogen gas-flow cryostat with temperature stability of about 1 K. The measurements were performed on a cylindrical thin disk (diameter/thickness = 5), whose plane contains both the tetragonal [001] axis and the [110] axis perpendicular to it. The orientation of the sample was controlled by a programmable goniometer in 5° steps during a full rotation of the magnetic field in the plane of the cylindrical disk at selected temperatures: 250, 300, 350, and 380 K. To obtain the uniaxial anisotropy parameter K_u at these temperatures, the angular dependence of the resonance field was fitted using the Smit–Suhl formula,^[49] similarly to the procedure followed in ref. [38].

LTEM Measurement: For LTEM measurements, (001) thin plates with various thickness were thinned from bulk single crystals by a focused ion beam system (NB5000, Hitachi); $t \approx 70$, 110, 150, 180, and 240 nm for (Fe_{0.60}Ni_{0.32}Rh_{0.08})₃P; $t \approx 80$, 140, 170, 190, and 220 nm for (Fe_{0.63}Ni_{0.33}Pd_{0.04})₃P; $t \approx 50$, 70, 100, 130, 160, and 210 nm for (Fe_{0.63}Ni_{0.30}Pd_{0.07})₃P. LTEM measurements were performed with a transmission electron microscope (JEM-2100F, JEOL) equipped with a double-tilt liquid-nitrogen holder (Gatan 636) and a double-tilt heating holder (Protochips: Fusion select). External magnetic fields applied to the (001) plates were obtained by tuning the objective lens current

of JEM-2100F, which were parallel to the incident electron beam. The distribution of in-plane magnetic induction fields was obtained by a TIE analysis using over- and under-focus LTEM images.^[50]

Micromagnetic Simulations: For the theoretical description of the magnetization the same continuum model as in ref. [14] was considered, that is, including the magnetic stiffness A_{ex} , S_4 -symmetric DMI, uniaxial anisotropy K_{μ} , Zeeman field H, and dipolar interactions due to the saturation magnetization $M_{\rm s}$. For the numerical implementation, the modified version of MuMax3^[51,52] was used in which the sign of the derivatives in the DMI-field was flipped in one spatial direction. Thus, the DMI favored right-handed helices in the horizontal direction and left-handed helices in the vertical direction. The micromagnetic parameters were chosen as $A_{ex} = 8.1 \text{ pJ m}^{-1}$, $D = 0.2 \text{ mJ m}^{-2}$, and $M_s =$ 600 kA m⁻¹. For obtaining the results in Figure 7, a triangular lattice of antiskyrmions was first relaxed at zero temperature at some convenient values of the magnetic field and anisotropy. The simulated system with periodic boundary conditions in the xy-plane measured 800 nm \times 700 nm \times 100 nm, discretized on 128 \times 112 \times 32 lattice sites, and contained 4 antiskyrmions. In a second step, this texture was used as the starting point for simulations at finite temperature T (T = 600 K) for a timespan *t* after which the textures appeared to be in quasi-equilibrium (t = 10 ns). This method yielded an approximation for the energetically most favorable texture which otherwise was a complex high-dimensional optimization problem with many local minima. The resulting thicknessaveraged magnetization is shown in Figure 7 together with the skyrmion number which was the 2D winding number^[53] up to a sign. The dipolar energy density $E_d = 66$ kJ m⁻³ was determined by deterministically finding the optimized helical wavelength at every value of the anisotropy which turned out to be qualitatively constant in the regime of interest.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

The authors thank R. Arita for fruitful discussions. The authors are grateful to V. Tsurkan and L. Prodan for preparation of the cylindrical thin disk for FMR measurements. This work was supported by JSPS Grantin-Aids for Scientific Research (Grant no. 19H00660, 20K15164) and JST CREST (Grant no. JPMJCR20T1 and JPMJCR1874) and via the DFG Priority Program SPP2137, Skyrmionics, under Grant nos. KE 2370/1-1. M.H. and H.-A.K.v.N. acknowledge funding within the Joint RFBR-DFG Research Project Contracts no. 19-51-45001 and no. KR2254/3-1. J.M. was supported as Humboldt/JSPS International Research Fellow (19F19815) and by the Alexander von Humboldt Foundation as a Feodor Lynen Return Fellow.

Note: Equation (1) was corrected on March 17, 2022, following a typesetting error on initial publication in Early View.

Conflict of Interest

The authors declare no conflict of interest.

Data Availability Statement

The data that support the findings of this study are available from the corresponding author upon reasonable request.

- C. Back, V. Cros, H. Ebert, K. Everschor-Sitte, A. Fert, M. Garst, T. Ma, S. Mankovsky, T. L. Monchesky, M. Mostovoy, N. Nagaosa, S. S. P. Parkin, C. Pfleiderer, N. Reyren, A. Rosch, Y. Taguchi, Y. Tokura, K. von Bergmann, J. Zang, J. Phys. D: Appl. Phys. 2020, 53, 363001.
- [2] Y. Tokura, N. Kanazawa, Chem. Rev. 2021, 121, 2857.
- [3] S. Mühlbauer, B. Binz, F. Jonietz, C. Pfleiderer, A. Rosch, A. Neubauer, R. Georgii, P. Böni, *Science* 2009, 323, 915.
- [4] X. Z. Yu, Y. Onose, N. Kanazawa, J. H. Park, J. H. Han, Y. Matsui, N. Nagaosa, Y. Tokura, *Nature* **2010**, *465*, 901.
- [5] S. Seki, X. Z. Yu, S. Ishiwata, Y. Tokura, Science 2012, 336, 198.
- [6] Y. Tokunaga, X. Z. Yu, J. S. White, H. M. Rønnow, D. Morikawa, Y. Taguchi, Y. Tokura, Nat. Commun. 2015, 6, 7638.
- [7] W. Li, C. Jin, R. Che, W. Wei, L. Lin, H. Du, M. Tian, J. Zang, *Phys. Rev. B* 2016, *93*, 060409(R).
- [8] I. Kézsmárki, S. Bordács, P. Milde, E. Neuber, L. M. Eng, J. S. White, H. M. Rønnow, C. D. Dewhurst, M. Mochizuki, K. Yanai, H. D. Ehlers, V. Tsurkan, A. Loidl, *Nat. Mater.* **2015**, *14*, 1116.
- [9] T. Kurumaji, T. Nakajima, V. Ukleev, A. Feoktystov, T. Arima, K. Kakurai, Y. Tokura, *Phys. Rev. Lett.* **2017**, *119*, 237201.
- [10] A. N. Bogdanov, D. A. Yablonskii, Sov. Phys. JETP 1989, 68, 101.
- [11] A. O. Leonov, T. L. Monchesky, N. Romming, A. Kubetzka, A. N. Bogdanov, R. Wiesendanger, *New J. Phys.* 2016, *18*, 065003.
- [12] A. K. Nayak, V. Kumar, T. Ma, P. Werner, E. Pippel, R. Sahoo, F. Damay, U. K. Rößler, C. Felser, S. S. P. Parkin, *Nature* **2017**, *548*, 561.

- [13] L. C. Peng, R. Takagi, W. Koshibae, K. Shibata, K. Nakajima, T. Arima, N. Nagaosa, S. Seki, X. Z. Yu, Y. Tokura, *Nat. Nanotechnol.* 2020, 15, 181.
- [14] K. Karube, L. C. Peng, J. Masell, X. Z. Yu, F. Kagawa, Y. Tokura, Y. Taguchi, *Nat. Mater.* **2021**, *20*, 335.
- [15] M. Heigl, S. Koraltan, M. Vaňatka, R. Kraft, C. Abert, C. Vogler, A. Semisalova, P. Che, A. Ullrich, T. Schmidt, J. Hintermayr, D. Grundler, M. Farle, M. Urbánek, D. Suess, M. Albrecht, *Nat. Commun.* 2021, *12*, 2611.
- [16] J. Jena, B. Göbel, T. Ma, V. Kumar, R. Saha, I. Mertig, C. Felser, S. S. P. Parkin, *Nat. Commun.* **2020**, *11*, 1115.
- [17] L. Camosi, N. Rougemaille, O. Fruchart, J. Vogel, S. Rohart, *Phys. Rev. B* 2018, 97, 134404.
- [18] A. P. Malozemoff, J. C. Slonczewski, Magnetic Domain Walls in Bubble Materials, Academic Press, New York 1979.
- [19] T. Ma, A. K. Sharma, R. Saha, A. K. Srivastava, P. Werner, P. Vir, V. Kumar, C. Felser, S. S. P. Parkin, *Adv. Mater.* **2020**, *32*, 2002043.
- [20] A. S. Sukhanov, B. E. Z. Cespedes, P. Vir, A. S. Cameron, A. Heinemann, N. Martin, G. Chaboussant, V. Kumar, P. Milde, L. M. Eng, C. Felser, D. S. Inosov, *Phys. Rev. B* **2020**, *102*, 174447.
- [21] A. Hubert, R. Schäfer, Magnetic Domains: The Analysis of Magnetic Microstructures, Springer, Berlin 1998.
- [22] M. Goto, H. Tange, T. Tokunaga, H. Fujii, T. Okamoto, Jpn. J. Appl. Phys. 1977, 16, 2175.
- [23] H. Shima, K. Oikawa, A. Fujita, K. Fukamichi, K. Ishida, A. Sakuma, *Phys. Rev. B* 2004, 70, 224408.
- [24] R. J. Gambino, T. R. McGuire, Y. Nakamura, J. Appl. Phys. 1967, 38, 1253.
- [25] H.-p. Liu, P. James, A. Broddefalk, Y. Andersson, P. Granberg, O. Eriksson, J. Magn. Magn. Mater. 1998, 189, 69.
- [26] A. Broddefalk, P. James, H.-p. Liu, B. Kalska, Y. Andersson, P. Granberg, P. Nordblad, L. Häggström, O. Eriksson, *Phys. Rev. B* 2000, 61, 413.
- [27] A. Broddefalk, P. Granberg, P. Nordblad, H.-p. Liu, Y. Andersson, J. Appl. Phys. **1998**, 83, 6980.
- [28] M. A. McGuire, H. Cao, B. C. Chakoumakos, B. C. Sales, *Phys. Rev.* B 2014, 90, 174425.
- [29] Q. Wang, S. S. Sun, X. Zhang, F. Pang, H. C. Lei, Phys. Rev. B 2016, 94, 075135.
- [30] G. He, L. Peis, R. Stumberger, L. Prodan, V. Tsurkan, N. Unglert, L. Chioncel, I. Kézsmárki, R. Hackl, *Phys. Status Solidi B* 2021, 2100169.
- [31] P. Vir, N. Kumar, H. Borrmann, B. Jamijansuren, G. Kreiner, C. Shekhar, C. Felser, *Chem. Mater.* 2019, *31*, 5876.
- [32] J. H. van Vleck, Phys. Rev. 1937, 52, 1178.
- [33] C. Zener, Phys. Rev. 1954, 96, 1335.
- [34] H. B. Callen, E. Callen, J. Phys. Chem. Solids 1966, 27, 1271.
- [35] W. Szmaja, J. Magn. Magn. Mater. 2006, 301, 546.
- [36] B. E. Z. Cespedes, P. Vir, P. Milde, C. Felser, L. M. Eng, Phys. Rev. B 2021, 103, 184411.
- [37] M. Preißinger, K. Karube, D. Ehlers, B. Szigeti, H.-A. Krug von Nidda, J. S. White, V. Ukleev, H. M. Rønnow, Y. Tokunaga, A. Kikkawa, Y. Tokura, Y. Taguchi, I. Kézsmárki, *npj Quantum Mater.* 2021, 6, 65.
- [38] D. Ehlers, I. Stasinopoulos, I. Kézsmárki, T. Fehér, V. Tsurkan, H.-A. Krug von Nidda, D. Grundler, A. Loidl, J. Phys.: Condens. Matter 2017, 29, 065803.
- [39] S. Goel, L. D. Anh, N. T. Tu, S. Ohya, M. Tanaka, Phys. Rev. Mater. 2019, 3, 084417.
- [40] K. Shibata, J. Iwasaki, N. Kanazawa, S. Aizawa, T. Tanigaki, M. Shirai, T. Nakajima, M. Kubota, M. Kawasaki, H. S. Park, D. Shindo, N. Nagaosa, Y. Tokura, *Nat. Nanotechnol.* **2015**, *10*, 589.
- [41] B. Cui, D. Yu, Z. Shao, Y. Liu, H. Wu, P. Nan, Z. Zhu, C. Wu, T. Guo, P. Chen, H.-A. Zhou, L. Xi, W. Jiang, H. Wang, S. Liang, H. Du,

K. L. Wang, W. Wang, K. Wu, X. Han, G. Zhang, H. Yang, G. Yu, *Adv. Mater.* **2021**, *33*, 2006924.

- [42] H. Yang, A. Thiaville, S. Rohart, A. Fert, M. Chshiev, Phys. Rev. Lett. 2015, 115, 267210.
- [43] J. Cho, N.-H. Kim, S. Lee, J.-S. Kim, R. Lavrijsen, A. Solignac, Y. Yin, D.-S. Han, N. J. J. van Hoof, H. J. M. Swagten, B. Koopmans, C.-Y. You, *Nat. Commun.* **2015**, *6*, 7635.
- [44] R. Takagi, D. Morikawa, K. Karube, N. Kanazawa, K. Shibata, G. Tatara, Y. Tokunaga, T. Arima, Y. Taguchi, Y. Tokura, S. Seki, *Phys. Rev. B* 2017, 95, 220406 (R).
- [45] X. Z. Yu, M. Mostovoy, Y. Tokunaga, W. Zhang, K. Kimoto, Y. Matsui, Y. Kaneko, N. Nagaosa, Y. Tokura, *Proc. Natl. Acad. Sci.* U. S. A. **2012**, 109, 8856.
- [46] C. Kittel, Phys. Rev. 1946, 70, 965.

- [47] B. Göbel, A. Mook, J. Henk, I. Mertig, O. A. Tretiakov, Phys. Rev. B 2019, 99, 060407(R).
- [48] T. Nagase, Y.-G. So, H. Yasui, T. Ishida, H. K. Yoshida, Y. Tanaka, K. Saitoh, N. Ikarashi, Y. Kawaguchi, M. Kuwahara, M. Nagao, *Nat. Commun.* **2021**, *12*, 3490.
- [49] G. V. Skrotskii, L. V. Kurbatov, Phenomenological Theory of Ferromagnetic Resonance, Ferromagnetic Resonance (Ed: S. V. Vonsovskii), Pergamon Press, Oxford 1965.
- [50] K. Ishizuka, B. Allman, J. Electron Microsc. 2005, 54, 191.
- [51] A. Vansteenkiste, J. Leliaert, M. Dvornik, M. Helsen, F. Garcia-Sanchez, B. Van Waeyenberge, AIP Adv. 2014, 4, 107133.
- [52] J. Leliaert, J. Mulkers, J. De Clercq, A. Coene, M. Dvornik, B. Van Waeyenberge, AIP Adv. 2017, 7, 125010.
- [53] B. Berg, M. Lüscher, Nucl. Phys. B 1981, 190, 412.