



Zentrum für Technomathematik

Fachbereich 3 – Mathematik und Informatik

A note on limitations of the use of accelerated concrete-carbonation tests for service-life predictions

A. Muntean, S. A. Meier, M. A. Peter,
M. Böhm, J. Kropp

Report 05–04

Berichte aus der Technomathematik

Report 05–04

April 2005

A note on limitations of the use of accelerated concrete-carbonation tests for service-life predictions

Adrian Muntean* Sebastian A. Meier* Malte A. Peter*
Michael Böhm* Jörg Kropp†

Abstract

Concrete carbonation is a process that can limit the lifetime of reinforced concrete structures. The resistance of concrete samples to carbonation is usually determined by accelerated tests under relatively high CO₂-concentrations and a fixed relative humidity. No general agreement exists on *whether* and *how* the results of these experiments can be extrapolated to a natural setting. This note presents a partial review of existing extrapolation strategies, particularly of explicit prediction formulas. A summary of the problems and limitations which are known from experiments and theoretical modelling is given. Special focus is directed to the different moisture transport characteristics in both natural and accelerated settings. Some strategies are proposed on how to deal with the problems.

Key words and phrases: Concrete carbonation, accelerated test, natural exposure, moisture, mathematical modelling, service-life prediction, extrapolation procedures and their limitations

Acknowledgements: The authors kindly acknowledge the support of the Deutsche Forschungsgemeinschaft (DFG) with a grant through the special priority program SPP1122 *Prediction of the Course of Physicochemical Damage Processes Involving Mineral Materials*.

1 Introduction

A common problem with reinforced concrete structures is the deterioration brought in by the corrosion of reinforcing steel and the subsequent spalling of concrete. This is most often caused by moisture and aggressive species (like Cl⁻, SO₄²⁻ etc.) advancing to the location of the steel reinforcements where it causes the corrosion. This process is often aggravated by carbonation, which is the result of the action of environmental conditions bringing about a drop in the alkalinity of the concrete over many years.

In order to measure a significant carbonation penetration in concrete-based materials in a short time interval, accelerated test methods have been proposed. Compare [Par90, CSK91], e.g., for an assessment of various methods of measuring the depth of carbonation. The need to determine the depth of carbonation requires a deep understanding of the limitations of the tests used to detect carbonation and of the meaning of the test results. Relying on such information, strategies capable of extrapolating the results of accelerated tests to outdoor carbonation conditions have to be proposed. Unfortunately, no general agreement exists on *whether* and *how* the results of these experiments can be extrapolated to a natural setting.

The scope of the present work is to give a *partial review of existing extrapolation strategies* (namely of complex models and explicit prediction formulas) as well as some of their drawbacks. It aims to complete other reviews already existing in the literature (compare sections 4.1 and 3.1).

*Centre for Industrial Mathematics, FB 3, University of Bremen, Postfach 330 440, 28334 Bremen

†University of Applied Sciences, FB 3 Civil Engineering (BAU), Neustadtswall 30, 28199 Bremen

The note is organised as follows: A brief motivation and description of the accelerated tests and their setup is presented in section 2. Several theoretical and semi-empirical models are concisely mentioned in section 3. Section 4 contains a summary of problems and limitations which are observed in experiments and are underlined by theoretical modelling. Special attention is paid to the different moisture transport characteristics in both natural and accelerated settings. A few strategies how to deal with the problems are proposed in section 5. We conclude this review by a short summary (section 6).

2 Accelerated carbonation tests

2.1 Why accelerated tests?

It is nearly impossible to reproduce natural exposure conditions by means of a simple test method. However, once the accelerated tests are performed, their results can offer useful information for real-time prediction provided that the limitations of the testing conditions are known. Unfortunately it is very often not clear how this information should be interpreted (extrapolated). Besides this predictive feature, the accelerated tests represent a way to investigate a series of extreme carbonation-related behaviours (e.g., carbonation does not take place, carbonation is extremely fast, a clogging situation occurs, etc.). On the other hand, it constitutes an appropriate framework (a comparative tool) to compare the quality of several types and treatments of concretes (curing time, water-to-cement ratio, etc.) in what the carbonation penetration is concerned.

2.2 Some test details

Detailed description of accelerated tests are given, for instance, in the EU standard¹ [Eur98], but also in [Kro83, Bie88, Bun94, Sis04, CSK91], and some of the references therein². A phenolphthalein colour test can be used to estimate the depth of carbonation by testing the pH of concrete (carbonation reduces pH). Upon application of the phenolphthalein solution to a freshly fractured or freshly cut surface of concrete, noncarbonated areas turn red or purple while carbonated areas remain colourless. Sampling can allow the average and standard deviation of the carbonation depth to be calculated. If the carbonation depth is compared with the average width of reinforcement cover, then the amount of potentially depassivated steel can be estimated.

In some aggregates, accurate phenolphthalein readings are difficult to obtain. Some concrete mixes are dark in colour and a colour change may not be visible. Care must be taken that no contamination of the surface occurs from dust and the phenolphthalein sprayed surface must be freshly exposed or it may be carbonated before testing. It is also possible for the phenolphthalein to bleach at very high pH, e.g. after electrochemical chloride extraction or realkalisation. If the sample is left for a few hours, it will turn pink. There can also be problems on buried structures where carbonation by ground water does not always produce the clear carbonation front induced by atmospheric carbon dioxide ingress.

¹Observe that this standard explains *how* an accelerated test should be done, but it does neither say *how* nor *whether* one should extrapolate the test results to natural conditions.

²In case of an accelerated carbonation test, it is worth noting that the humidity, temperature, and the CO₂ concentration level in the carbonation chamber are monitorised. *Accelerated* basically means that the CO₂ concentration in the chamber is essentially higher than in a normal atmospheric situation. Note that usually constant conditions are imposed. In most of the situations, two main *assumptions* are taken into consideration: (1) The relative humidity of the sample equals that of the carbonation chamber; (2) The hydration reactions are complete (or *almost* complete).

3 Extrapolation methods

Cf. [SAC03], no general agreement exists on *how* to extrapolate the penetration depths measured in an accelerated test to a natural setting. There are various models in the literature which can be roughly split in two conceptually different categories: The *explicit laws* for the penetration depth have a longer history. They are based on either empirical or theoretical considerations, or on a mixture of both. In contrast, there are *complex models* that usually consist of systems of partial differential equations modelling the full carbonation process. Explicit solutions for these models exist only in very special cases, therefore in general they have to be solved numerically.

3.1 Explicit prediction formulas

In practice, those models are preferred which are easy to handle. Usually they consist of *one explicit formula* predicting the carbonation depth at a given time t . They are sometimes called *carbonation laws*. However, they can only hold under several strong assumptions and it is not at all obvious how certain parameters like the cement type or the water-to-cement ratio enter into the coefficients.

The most often used carbonation law is the so-called *standard- \sqrt{t} -law*. Based on Fick's first law of diffusion, the carbonation depth at time t , which we denote by $s(t)$, is given by

$$s(t) = \sqrt{\frac{2D_{\text{CO}_2}[\text{CO}_2]t}{[\text{Ca}(\text{OH})_2]}}, \quad \text{for all } t > 0. \quad (1)$$

In (1), the coefficient D_{CO_2} represents the effective diffusivity of gaseous CO_2 whereas $[\text{Ca}(\text{OH})_2]$ is the initial amount of $\text{Ca}(\text{OH})_2$ that can react with CO_2 .³ The above law can be derived as a *pseudo-steady-state solution* of a reaction-diffusion model if an instantaneous reaction of CO_2 with the $\text{Ca}(\text{OH})_2$ available by dissolution is assumed. See [Kro95, Sis04], e.g., for such a derivation. Absorption delays for CO_2 , moisture effects, and transport of other species than gaseous CO_2 are neglected.

A generalisation of (1) is given by Papadakis et al. [PVF89]. In their study, they include a late stage of hydration reactions as well as additional carbonation reactions of CSH, C_2S , and C_3S and they give explicit conditions for the pseudo-steady-state approximation (PSSA) to be valid. Their approach leads to the following expression to estimate the penetration depth

$$s(t) = \sqrt{\frac{2D_{\text{CO}_2}[\text{CO}_2]t}{[\text{Ca}(\text{OH})_2] + 3[\text{CSH}] + 3[\text{C}_2\text{S}] + 3[\text{C}_3\text{S}]}, \quad \text{for all } t > 0. \quad (2)$$

Some authors have proposed modifications of the \sqrt{t} -law (1) due to empirical or theoretical considerations. Sisomphon [Sis04, Sis05] observes a better fitting to his measured penetration depths with an exponent of $n = 0.4$. Therefore, the law

$$s(t) = \sqrt{\frac{2D_{\text{CO}_2}[\text{CO}_2]}{[\text{Ca}(\text{OH})_2]}} t^{0.4}, \quad \text{for all } t > 0, \quad (3)$$

is used for prediction. The deviation from (1) is explained by the pore reduction due to carbonation. See section 4.2.1. Using atmospheric conditions of 3% CO_2 in the acceleration chamber, an acceleration of the penetration by roughly a factor of 10 is obtained. In contrast, Parrott [Par92] relates the exponent n empirically to the relative humidity in the chamber, i.e. $n = f(\text{RH})$.

Note that the seemingly small changes in the exponent cause a dramatic change in the prediction. Using the *equivalent testing time* notion⁴ we denote by t^{real} the time needed to carbonate

³To be more precise, the quantity $[A]$ in (1)–(3) denotes the initial concentration of species A. This is assumed to be completely available to the carbonation reaction.

⁴This was introduced by Ho and Lewis, e.g. See [SAC03, HL87].

1 cm of a concrete specimen under natural conditions (0.03% CO₂), and by t^{acc} the respective time in an accelerated chamber with 3% CO₂. Then by (3) we obtain

$$t^{\text{real}} = 316 t^{\text{acc}}. \quad (4)$$

On the other hand, using (1) or (2) we obtain

$$t^{\text{real}} = 100 t^{\text{acc}}. \quad (5)$$

The obvious question arises: *Which prediction is the appropriate one?*

Two other theoretical models should also be mentioned: The model by Bakker [Bak64] is also based on a steady-state assumption and includes *drying phases* during which no carbonation can occur. See also section 4.2. The model by Tuutti [Tuu82] is a non-steady-state approximation based on moving boundaries. Further approaches have been developed by Hilsdorf et al. [MC99] and Schießl [Sch76]. Besides the semi-empirical and asymptotic approaches, some semi-analytic techniques have also been employed to predict the penetration depths. See [LL03], e.g. Due to the complexity of the full carbonation problem, their success is somehow limited. For still more models we refer to the overviews in [Kro95, SAC03, Cha99, Bun94], e.g. See also the list of carbonation laws in [Sis04], table 2.2, p. 30.

It should be noted that there are not only a variety of models, but also various possible ways how to use them. For example, the standard- \sqrt{t} -law can be used for prediction without any testing method if the values of $[\text{Ca}(\text{OH})_2]$ and D_{CO_2} are known. Since particularly the latter parameter is usually difficult to measure, it is nevertheless common to assume the structure $s(t) = k\sqrt{[\text{CO}_2]t}$ and to fit the parameter k to the measurements in the accelerated test.

3.2 Complex models

In the last decades, large models have been developed in order to simulate the carbonation process numerically. The general approach is to collect mass balances (and possibly momentum and heat balances) of the active species. This procedure yields coupled systems of conservation laws (usually, ordinary and partial differential equations). We call them generically *isoline models*. For more details on isoline approaches of the carbonation problem, see the contributions by Roelfstra et al. [HRW83], Saetta et al. [SSV93], Papadakis et al. [PVF89], Maekawa et al. [MIK03], Bary and Sellier [BS04], etc. See also [MPMB05, PMMB05]. Numerical simulations in 2D have been done by Saetta et al. [SSV95, SV04], Steffens [Ste00], Burkan Isgor [Isg01], and Schmidt et al. [SMB05]. As far as we are aware of, simulations of concrete carbonation in 3D have not been done yet.

Since in both settings (accelerated and natural) the reaction part dominates the transport, in most cases a relatively thin reaction zone is initially formed which separates the carbonated region from the uncarbonated region and travels into the material. The observation of this pattern formation (an internal more or less sharp *reaction layer*) motivates the introduction of conceptually different models to describe the dynamics of this internal layer. We refer to them shortly as *moving-boundary models* or *moving-interface models*. Such models have been proposed for carbonation by Tuutti [Tuu82], Brieger and Wittmann [BW86], and by Böhm et al. [BKM03b, BKM03a] and Muntean [Mun05]. For more details on the latter approach, see also [MB04b, GM03, MB04a].

Most of the models are based on macroscale formulations. Such macromodels usually arise from exact micromodels by averaging techniques like periodic homogenisation (see [CD99], e.g.) or the volume averaging method by Whitaker [Whi99]. See particularly [SMB99, SMSB05] for an application of the latter method to concrete-based materials. By the first method, a variety of mixed *micro-macro models* can also arise where microstructure effects are described by a local cell problem. See [Mei04, Pet03] for applications to the concrete carbonation problem. Such models can capture effects on numerous spatial scales such as different pore sizes in cement-based materials or fractures.

The effective usage of a complex model combining measured data from accelerated tests for prediction purposes is nontrivial. Particularly, it leads to *parameter identification problems*. See,

e.g., [BK89] and references therein for a general overview. This subject has not been treated in detail for the carbonation problem, at least to our knowledge.

4 Problems and limitations

4.1 Comparisons in the literature

Unfortunately there are very few experimental works, in which the authors directly compare results of accelerated tests with those under natural conditions. We are not aware of extensive studies where several different external CO₂-concentrations and several RH levels are imposed on samples having identical chemical composition and also same mixing/curing/drying (hydration degree) treatment. However, there are many hints in the experimental work indicating that accelerated carbonation tests cannot be extrapolated to a natural-exposure scenario by a simple scaling only related to the ratio of the CO₂-concentrations.

Andrade et al. [SAC03] compare the carbonation of a set of concrete samples under natural and accelerated (5% and 100% CO₂) testing conditions. Roughly, they obtain a propagation of the carbonation depth which is 5 and 40 times faster, respectively, than in the natural case. A comparison with the theoretical models by Tuutti [Tuu82] and Bakker [Bak64] and with the empirical model by Parrott [Par94] shows that the models are in the right range but overestimate the carbonation penetration. Additionally, some contradictory trends are illustrated when different types of additions are used. It is emphasised that predictions should only be made between the same types of concretes. Moreover, they conclude that experimental results with 4 – 5% CO₂ cannot be simply extrapolated to larger values of CO₂. Similar effects have been observed by Ishida et al. [IMS04] by means of numerical simulations. The authors investigate the behaviour of their model under different CO₂ concentrations and also with different additions in the concrete. They conclude that accelerated and natural tests are not always analogous.

Note that even in those references, where a simple scaling between the two tests is assumed, there is no agreement about the choice of the factors by which carbonation advancement is increased or decreased. See [Ver58, HL87], e.g. Papadakis et al. [PVF89] also compare the case of experimental data where different atmospheric CO₂-concentrations are successively imposed in the carbonation chamber. In their case, the measurements seem to be in excellent agreement with the law (2) for the carbonation penetration proposed in the same paper. On the other hand, Chaussadent [Cha97] reports experimental results where a high CO₂ content in the atmosphere even leads to a slower carbonation rate.

4.2 Possible causes of discrepancies

There are several physico-chemical processes, exposure conditions, and parameters, which can show a different behaviour under accelerated compared to natural conditions. There are two significant (technical) differences that appear in the setup of accelerated tests: (1) The type of exposure conditions (higher CO₂ level than it is expected in the atmospheric conditions, constant relative humidity, fixed temperature, etc.), and (2) the shorter duration of the whole process. The first fact is somehow more obvious, whereas the latter one can produce some hidden effects. In the following subsections, we try to review the most important discrepancies between the two test methods. They are all somehow well-known by the community dealing with this subject. However, a lot of effects are concurring and the precise interplay is *not* known such that even general trends are extensively discussed and *differently interpreted* in the literature. Note also that there may still be further effects that are not considered here.

4.2.1 Changes in the microstructure due to carbonation

Besides the decrease in pH, another important consequence of the carbonation process is the change induced in the microstructure. A detailed description of this phenomenon can be found, for instance, in [BKH87, NP97, CBBH⁺00, Bie88]. In particular, at least in the case of ordinary-Portland-cement-based materials (OPC), the fast precipitation of the CaCO_3 produced by carbonation can lead step by step to a clogging of the pores. This locally hinders any further transport of CO_2 . Macroscopically, the clogging of the pores can be numerically captured by including a porosity variable in the models which can vary in time or even in space. See existing porosity models in [PVF89, SON90, MIK03] (linear relationships), [MPMB05] (exponential decay), [BS04, Ort94] (dynamical models), e.g. Alternatively, a time-dependent effective transport coefficient for gaseous CO_2 can be used. It is assumed [Sis04] that due to a decrease in porosity a standard \sqrt{t} -law will overestimate the carbonation for large times.

In [CSH05], the authors observe experimentally that in the accelerated test a prolific development of calcite crystals takes place in the pores and fissures through which the carbonic anhydride flows. On the other hand, under natural conditions carbonation is much slower and similar levels of crystals development are not reached (at least not within 6 months).

4.2.2 Effects of other reactions

There are several chemical reactions inside the concrete competing with the carbonation of $\text{Ca}(\text{OH})_2$. By *competing* it is meant that partially the same reactants are involved, for instance CO_2 or CSH, e.g., to deplete $\text{Ca}(\text{OH})_2$. They also have an implicit impact on the carbonation process by altering the microstructure and consequently the transport properties.

- *Competition between CSH and $\text{Ca}(\text{OH})_2$ carbonation*

In case of samples with OPC (in both acc. and nat. testing conditions), a competition between the carbonation of CSH phases and that of $\text{Ca}(\text{OH})_2$ always exists. It is however not always clear whether this competition is strong, or whether the CSH phases are really accessible to CO_2 or not. If they are, then their carbonation has to be investigated in parallel to the bulk carbonation. See [PVF89, PMMB05, Ste00], e.g.

- *Competition of a late stage of hydration, with the carbonation of CSH phases and $\text{Ca}(\text{OH})_2$*

In accelerated tests, one usually assumes the hydration to be complete. If this limitation is not satisfied (as it is usually the case for natural carbonation), then an additional competition of C_2S and C_3S with CSH and $\text{Ca}(\text{OH})_2$ may occur. See [PVF91, PVF89, PMMB05, Par85].

- *Effect of nonreacting additions on $\text{Ca}(\text{OH})_2$ carbonation*

In some cases, mineral additions like

- (a) blast furnace slag,
- (b) pozzolanic additions (fly ash, silica fume, e.g.),
- (c) or something else (biologic materials, e.g.)

are added in order to obtain samples with improved mechanical properties. In concrete-based materials containing (a), the carbonation process is simply faster than in OPC materials. This follows the rule *more slag, less $\text{Ca}(\text{OH})_2$* . We concisely discuss the case (b) in the next item. We do not address our attention to case (c).

- *Competition of a late stage of hydration and pozzolanic reactions with the carbonation of CSH phases and of $\text{Ca}(\text{OH})_2$*

Although the complex chemistry of such scenarios is quite well understood, the interplay between hydration, pozzolanic, and carbonation reactions with the underlying transport mechanisms (especially for case (b) above) is not completely understood. It may finally result

in a fast carbonation. Furthermore, it is not obvious how the concrete porosity evolves in such cases. The evolution of the porosity (in time and space variables) seems to be determined by the complex competition between several reactions depleting $\text{Ca}(\text{OH})_2$, and the difference in the molar volumes of $\text{Ca}(\text{OH})_2$ and calcite-based products. See, e.g., [Sis04, FS04] for experimental data and modelling, [PVF89, PVF92, PVF91] and [Bie88, Tay97, KS87] for more on chemistry.

- *Related competition scenarios*

Other alkaline species than $\text{Ca}(\text{OH})_2$ may produce calcium carbonates. Depending on the chemistry of the cement paste, KOH , NaOH , and $\text{Mg}(\text{OH})_2$, e.g., may be available to the reaction with CO_2 . See [Ste00], e.g., for a short account of the corresponding carbonation reactions.

4.2.3 Production of moisture by the carbonation reaction

Besides calcium carbonate, water is produced by the carbonation reaction. In general, a mole ratio of 1:1 of *water released* to *carbon dioxide reacted* is assumed. This water joins the amount of water that is already present in the concrete sample from mixing and curing. Under natural conditions, the low reaction gives the released water enough time to diffuse and leave the specimen (if we assume a lower RH level outside the sample). Therefore, if the structure is sheltered from rain, after a long-term carbonation process the sample will be almost completely dried out. In accelerated tests, when a comparable depth of carbonation is reached, the humidity is still very high. This simply suggests that the humidity does not have sufficient time to leave the sample. At the initial stage, this can even lead to large moisture gradients or a *layer of water* near the exposed surface where the pores are almost saturated. This was particularly observed via numerical simulations in [MPMB05]. Figure 1 shows examples of moisture profiles within a concrete sample during an accelerated test (left) and under natural conditions (right). In the accelerated setting, the moisture concentration exhibits significantly larger values in the already carbonated zone. Similar moisture profiles were also obtained by simulations in [IMS04] and [BS04], e.g.




Figure 1: Numerical prediction of moisture profiles under accelerated and natural conditions. Left: Accelerated test, $\text{CO}_2 = 50\%$, $\text{RH} = 65\%$ (cf. [PVF89]). Right: Natural test, $\text{CO}_2 = 0.03\%$, $\text{RH} = 78\%$ (cf. [Wie84]).

Consequently, the carbonation process becomes slower as the gaseous CO_2 is hindered to progress to the reaction zone. This feature was also reported in [IMS04, Ish05] based on numerical simulations, and experimentally in [SAC03] by measuring the weight changes during carbonation. At a later stage, this water layer may be reduced due to evaporation from the surface of the specimen. Cf. [IMS04], an opposite effect may then occur as a larger amount of water has been stored inside the concrete specimen. Such humidity may facilitate the bulk carbonation reaction by offering a proper reaction medium, hence probably depleting more $\text{Ca}(\text{OH})_2$. The saturation of pores due to water released by carbonation is mentioned by various authors, for instance [Cha97, SSV95, Ver58, CSH05]. See also [Par92, GK03, Mun04] for some discussions on the modelling of moisture in concrete and/or the complex inter-dynamics between moisture effects and the chemistry of carbonation.

4.2.4 Effects of heat production by carbonation

It was reported (cf. [CSH05], e.g.) that the increase in $\text{CO}_2(g)$ concentration increases the production rate by carbonation. Moreover, when 100% $\text{CO}_2(g)$ is used, the heat generated during reaction (about 74 kJ/mole) is so great that a premature drying of samples occurs, and hence (probably) not all the available calcium hydroxide is converted into calcium carbonate. Such a premature drying does not occur when the sample is exposed to natural conditions. Cf. [Cha99], e.g., the solubility of CO_2 in pore water, the production terms by the reactions, and the diffusivity of gaseous CO_2 are also strongly affected by variations in the temperature field. See also [FB90] or any other textbook on physical chemistry. The thermodynamical scenario at the micro-meso scale and its effects on the processes holding at the macroscale is too complex to be included here. A critical view on the mass-balance models (of moisture and involved chemical species), which account for non-isothermal conditions at the pore level and then at the macro level, is done in [BBS97], e.g. The temperature variations play a role in the models of carbonation described in [SSV93, Ste00], e.g.

4.2.5 Leaching of alkaline substances

Calcium hydroxide is one of the main products of the hydration reactions in concrete with Portland cement. It is also one of the more soluble phases of the hydrated parts. The influence of calcium hydroxide dissolution combined with leaching of the hydroxide and calcium ions from the pore water (if the sample is stored in pure water) leads to significant changes in the transport properties of the material. Note that, cf. [MBSM01], e.g., the leaching of calcium hydroxide usually increases the porosity of the concrete. This issue is also strongly related with the very long term durability of nuclear waste disposals. The existing literature on the latter subject is huge. We only refer to [Tor04] and the references therein. For details on modelling the basic mechanisms on which the leaching of $\text{Ca}(\text{OH})_2$ relies, see [Mai99, MU01, Kro95, Joh98, Bun94, BS04, Sch76], e.g.

Concerning the carbonation prediction problem, it is reported (cf. [GSK04], e.g.) that the pore water composition differs essentially when natural exposure conditions apply compared to the accelerated case. Note also that in the derivation of the standard- \sqrt{t} -law (1) the transport of $\text{Ca}(\text{OH})_2$ has been neglected. These facts indicate that the influence of leaching may not be comparable in accelerated and natural settings. Nevertheless, it is also reported that if carbonation takes place, then the tendency of the available $\text{Ca}(\text{OH})_2$ to leach out by dissolution is essentially diminished. More on the interplay between carbonation, dissolution, and leaching of $\text{Ca}(\text{OH})_2$ is dealt with in [GSK04, GGS⁺04] as well [BKM03b, BKM03a, MB04b, GM03, MB04a], e.g.

Related issues are: the leaching of CaCO_3 , drying/wetting cycles, the effect of a sealant, and the type of boundary conditions for $\text{Ca}(\text{OH})_2$.

4.2.6 Resistance to exchange with the environment

The various mechanisms by which the concrete specimen interacts with the surrounding environment are not quite clear. For a chemical species in the gaseous phase (such as $\text{CO}_2(g)$, e.g.) a Dirichlet boundary condition may describe the mass transfer at the exterior surface quite well. However, for moisture the situation can be rather complicated. See, e.g., [Gru97] and [Gru00]. Cf. [GK03], under specific conditions the drying of the concrete can become controlled by evaporation and diffusion of water vapour through a thin boundary layer near the exposed surface. Note that if a Robin boundary condition is used instead of a Dirichlet one, the classical derivation of the \sqrt{t} -law (for instance, via the Green's function technique for linear diffusion equations) leads to different results. In some cases, it may become reasonable to describe an accelerated test with a different type of boundary condition than a natural test.

4.2.7 Ambient moisture and temperature variations

In an outdoor scenario, the concrete sample is exposed to variations in the ambient humidity and temperature. The temperature is important as almost all relevant transport and reaction model parameters as well as absorption isotherms depend on a local thermic equilibrium. See [Ste00, Bun94, Sis04], e.g., for some details. Essentially varying the temperature field, it may occur that gradients of temperature start developing into the material. As a result of this, a heat equation, Soret and Dufour effects, and other specific phenomena couple with the reaction-transport part. Models for non-isothermal carbonation are considered in [BW86, HRW83, SSV93, SSV95, SV04, Ste00, Isg01], etc. The effect of seasonal humidity variations on the progress of the carbonation front are numerically investigated, for instance, in [Ste00, MPMB05]. The influence of humidity has been already discussed in sections 4.2.3 and 4.2.6. Very high as well as very low humidity levels are supposed to slow down the advancement of the front. The accelerated experiments are often performed at a fixed humidity level between 50 and 70%. As an example for a natural setting, in the north of Germany a varying humidity between 70 and 90% is measured. For most of the models described in section 3.1 it is not clear if and how a comparison can be done. In case of models that account for different moisture values a varying ambient humidity is usually replaced by its average in time (cf. [Arf98], e.g.).

Related aspects are: periodic vs. constant inputs, superposition of two or more time-periodic inputs profiles at the outer boundary (summer vs. winter, day vs. night, etc.).

4.2.8 Effect of precipitation (rainfall, e.g.)

If the concrete under natural conditions is not sheltered from precipitation, the results are even harder to compare to an accelerated setting. In a 40-months test, Houst and Wittmann [HW02] observe a significantly deeper CO₂-penetration at faces of a concrete sample which are sheltered from rain in comparison to faces which are directly exposed. See also the experiments by Wierig [Wie84]. It is assumed (cf. [Bun94, Cha99], e.g.) that due to rainfall the pores near the surface are completely saturated with water such that no CO₂ transport can happen. Consequently, the carbonation progress is interrupted by *drying periods* of a characteristic length. The Bakker model [Bak64] tries to account for this site-dependent effect.

5 Suggestions and strategies

In the previous section, a preliminary list of mechanisms has been discussed that usually complicate any interpretation of the carbonation process. Hence, they can lead to highly different results of tests under natural and accelerated conditions. We note that none of the existing models can account for *all* of these effects. This leads to essential limitations in the interpretation of accelerated tests results.

Further progress in the prediction of the carbonation penetration based on accelerated tests can be achieved following different strategies. We note some points which seem promising and partly necessary:

1. More experiments are needed in order to reach a better understanding of the carbonation process under various exposure conditions. In particular, experimental data, which refer to one concrete type, is needed for a variety of CO₂-concentrations and RH levels. Besides carbonation penetration depths, the measurements should also provide concentration profiles of CO₂, CaCO₃, and alkaline species for different times⁵. This lack of useful information is specifically emphasised by Andrade et al. in [SAC03].

⁵Four experimental points in the *penetration depth vs. time* curves contain almost no information about the carbonation process. If the whole carbonation process would be a purely diffusive process, then the four points might suffice. Here this is not the case. Much care has to be taken in setting up carbonation tests. For instance, the experimental points to be measured should be related to the number of free parameters defining the whole process.

2. Some of the limitations of existing explicit laws for predicting the carbonation penetration depth can be circumvented by means of mathematical modelling. For instance, Bakker's model is an approach to incorporate moisture effects, at least to some extent. Asymptotic studies can bring some more insight on the dynamics of the reaction layers (or zones) and their penetration into the material (see [BS00, Mai99], e.g.) and so on. These layers may refer to the carbonation reaction or to something else, like dissolution/precipitation reactions, e.g. Nondimensionalisation and appropriate scaling of large models are useful tools to reduce the number of involved model parameters. They can provide a basis to derive asymptotic solutions of simple models. The derivation of the relation (2) can serve as a basis for alike investigations. It might also be fruitful to base on the moving-boundary models in [BKM03b, BKM03a].

Surely, such asymptotic formulas can only be valid to a certain extent. They usually provide only a particular view (depending on one very small or very large parameter) on the involved processes. Nevertheless, they can help understanding the interconnection between several parallel processes. In cases where no analytical solution can be given, an asymptotic approximation may be an appropriate tool to check the correct behaviour and sometimes the accuracy of the numerical solution.

3. To obtain precise quantitative predictions, the use of numerical implementations of extensive theoretical models (like those from [SV04, Ste00, BKM03a, Gru00, MPMB05, PMMB05, SMB05], e.g.) is inevitable. Reliable methods have to be developed to fit the respective models with accessible data from accelerated tests. This leads to classical parameter identification problems. In most of the cases, such problems are ill-posed, and therefore, a conceptually simple identification procedure is not always possible. One way to deal numerically with such issues is offered by various existing shooting strategies. However, if such strategies are to be applied to large systems of nonlinear differential equations, many technical difficulties are expected to occur.
4. It has to be mentioned that the purely macroscopic models are not capable to include all microscopic effects described in section 4.2. Therefore the use of models incorporating microstructure effects can yield much more accurate prediction results. In addition, the mathematical tool of homogenisation can help identifying parameters in macromodels. In particular, the structure of the diffusion constant or *diffusion tensor* strongly depends on the local microstructure and is one of the key parameters for predicting the carbonation depth.

6 Summary

A review of extrapolation strategies from accelerated carbonation tests is presented. A set of possible limitations is summarised. These are theoretically predicted and/or experimentally observed. It is pointed out that some of the issues are inevitable, but some other could be circumvented by means of modelling. This note has a preliminary character. The elaboration of extrapolation strategies is planned in future work, for instance based on shooting strategies. The review of the problems in section 4 and the list of relevant references are also far from being complete.

References

- [Arf98] J. Arfvidsson. *Moisture Transport in Porous Media. Modelling Based on Kirchhoff Potentials*. PhD thesis, Department of Building Technology, Building Physics, Lund University, 1998. Report TVBH-1010.
- [Bak64] R. Bakker. Prediction of service life reinforcement in concrete under different climatic conditions at given cover. In R. M. Swamy, editor, *Corrosion and Protection of Steel in Concrete International Conference*, Sheffield, 1964.

- [BBS97] P. Baggio, C. Bonacina, and B. A. Schrefler. Some considerations on modeling heat and mass transfer in porous media. *Transport in Porous Media*, 28:233–251, 1997.
- [Bie88] Th. A. Bier. *Karbonatisierung und Realkalisierung von Zementstein und Beton*. PhD thesis, University Fridericiana in Karlsruhe, Karlsruhe, 1988. Schriftenreihe des Instituts für Massivbau und Baustofftechnologie. Editors: J. Eibl, H. K. Hilsdorf.
- [BK89] H. T. Banks and K. Kunisch. *Estimation Techniques for Distributed Parameter Systems*. Birkhäuser, 1989.
- [BKH87] Th. A. Bier, J. Kropp, and H. K. Hilsdorf. Carbonation and realkalization of concrete and hydrated cement paste. In J. C. Maso, editor, *Durability of construction materials*, volume 3. RILEM, Chapman & Hall Publishers, 1987.
- [BKM03a] M. Böhm, J. Kropp, and A. Muntean. A two-reaction-zones moving-interface model for predicting $\text{Ca}(\text{OH})_2$ -carbonation in concrete. Berichte aus der Technomathematik 03–04, ZeTeM, University of Bremen, 2003.
- [BKM03b] M. Böhm, J. Kropp, and A. Muntean. On a prediction model for concrete carbonation based on moving interfaces – Interface concentrated reactions. Berichte aus der Technomathematik 03–03, ZeTeM, University of Bremen, 2003.
- [BS00] M. Z. Bazant and H. A. Stone. Asymptotics of reaction-diffusion fronts with one static and one diffusing reactant. *Physica D*, 147:95–121, 2000.
- [BS04] B. Bary and A. Sellier. Coupled moisture-carbon dioxide-calcium transfer model for carbonation in concrete. *Cement and Concrete Research*, 34:1859–1872, 2004.
- [Bun94] D. Bunte. *Zum Karbonatisierungsbedingten Verlust der Dauerhaftigkeit von Außenbauteilen aus Stahlbeton*. PhD thesis, TU Braunschweig, 1994.
- [BW86] L. M. Brieger and F. H. Wittmann. Numerical simulation of concrete carbonation. In F. H. Wittmann, editor, *Werkstoffwissenschaften und Bausanierung. Berichtstand zum 2. Internationalen Kolloquium*, pages 635–640. Technical Academy Esslingen, 1986.
- [CBBH⁺00] T. Chaussadent, V. Baroghel-Bouny, H. Hornain, N. Rafai, and A. Ammouche. Effect of water-cement ratio of cement pastes on microstructural characteristics related to carbonation process. In V. M. Malhotra, editor, *Durability of concrete*, volume I of *Proceedings Fifth International Conference*, Barcelona, Spain, 2000.
- [CD99] D. Cioranescu and P. Donato. *An Introduction to Homogenization*. Oxford University Press, 1999.
- [Cha97] T. Chaussadent. Analyse des mécanismes de carbonatation du beton. In *AFPC-AFREM Durabilité des Betons "Méthodes recommandés pour la mesure des grandeurs associées à la durabilité"*, Compte-Rendus des Journées Techniques, pages 75–86, Toulouse, France, 1997. INSA Génie Civil.
- [Cha99] T. Chaussadent. États de lieux et réflexions sur la carbonatation du beton armé. Technical report, Laboratoire Central de Ponts et Chaussées, Paris, 1999.
- [CSH05] G. Cultrone, E. Sebastian, and M. Ortega Huertas. Forced and natural carbonation of lime-based mortars with and without additives: Mineralogical and textural changes. *Cement and Concrete Research*, 2005. in press.
- [CSK91] D. H. Campbell, R. D. Sturm, and S. H. Kosmatka. Detecting carbonation. *Concrete Technology Today*, 12(1):1–5, 1991. Portland Cement Association.

- [Eur98] European Committee for Standardization. *Product and systems for the protection and repair of concrete structures. Test methods. Determination of resistance to carbonation*, 1998. European Standard, prEN 13295.
- [FB90] G. F. Froment and K. B. Bischoff. *Chemical Reactor Analysis and Design*. Wiley Series in Chemical Engineering. John Wiley and Sons, 2nd edition, 1990.
- [FS04] L. Franke and K. Sisomphon. A new chemical method for analyzing free calcium hydroxide content in cementing material. *Cement and Concrete Research*, 34:1161–1165, 2004.
- [GGS⁺04] C. Gervais, A. C. Garrabrants, F. Sanchez, R. Barna, P. Moszkowicz, and D. S. Kosson. The effects of carbonation and drying during intermittent leaching on the release of inorganic constituents from a cement-based matrix. *Cement and Concrete Research*, 34:119–131, 2004.
- [GK03] A. C. Garrabrants and D. D. Kosson. Modeling moisture transport from a portland cement-based material during storage in reactive and inert atmospheres. *Drying Technology*, 21(5):775–805, 2003.
- [GM03] R. Grotmaack and A. Muntean. Stabilitätsanalyse eines Moving-Boundary-Modells der beschleunigten Karbonatisierung von Portlandzementen. Berichte aus der Technomathematik 03–12, ZeTeM, University of Bremen, 2003.
- [Gru97] J. Grunewald. *Diffusiver und konvektiver Stoff- und Energietransport in kapillarporösen Baustoffen*. PhD thesis, University of Technology Dresden, 1997.
- [Gru00] J. Grunewald. *Documentation of the numerical simulation program DIM3.1. Volume 1: Theoretical fundamentals*. Institute of Building Climatology, University of Technology Dresden, 2000.
- [GSK04] A. C. Garrabrants, F. Sanchez, and D. S. Kosson. Changes in constituent equilibrium leaching and pore water characteristics of a Portland cement mortar as a result of carbonation. *Waste Management*, 24:19–36, 2004.
- [HL87] D. W. S. Ho and R. K. Lewis. Carbonation of concrete and its prediction. *Cement and Concrete Research*, 17:489–504, 1987.
- [HRW83] Y. Houst, P. Roelfstra, and F. H. Wittmann. A model to predict service life of concrete structures. In *Proc. Int. Conf. Technical Academy Esslingen*, pages 181–186, 1983.
- [HW02] Y. F. Houst and F. H. Wittmann. Depth profiles of carbonates formed during natural carbonation. *Cement and Concrete Research*, 32:1923–1930, 2002.
- [IMS04] T. Ishida, K. Maekawa, and M. Soltani. Theoretically identified strong coupling of carbonation rate and thermodynamic moisture states in micropores of concrete. *Journal of Advanced Concrete Technology*, 2(2):213–222, 2004. Japan Concrete Institute.
- [Isg01] O. Burkan Isgor. *A durability model for chloride and carbonation induced steel corrosion in reinforced concrete members*. PhD thesis, Department of Civil and Environmental Engineering, Carleton University, Ottawa, Ontario, Canada, 2001.
- [Ish05] T. Ishida. Private communications, 2005.
- [Joh98] B. F. Johannesson. Modelling of transport processes involved in service life prediction of concrete. Important principles. Licentiate thesis, Division of Building Materials, Lund Institute of Technology, 1998.
- [Kro83] J. Kropp. *Karbonatisierung und Transportvorgänge in Zementstein*. PhD thesis, Karlsruhe University, 1983.

- [Kro95] J. Kropp. Relations between transport characteristics and durability. In J. Kropp and H. K. Hilsdorf, editors, *Performance Criteria for Concrete Durability*, RILEM Report 12, pages 97–137. E and FN Spon Editions, 1995.
- [KS87] H. Knoblauch and U. Schneider. *Bauchemie*. Werner Verlag, 1987.
- [LL03] M.-T. Liang and S.-M. Lin. Mathematical modeling and applications for concrete carbonation. *Journal of Marine Science and Technology*, 11(1):20–33, 2003.
- [Mai99] M. Mainguy. *Modèles de diffusion non-linéaires en milieux poreux. Application à la dissolution et au séchage des matériaux cimentaires*. Thèse de doctorat, École Nationale des Ponts et Chaussées, Paris, 1999.
- [MB04a] A. Muntean and M. Böhm. On a moving reaction layer model for the prediction of the service life of concrete structures. In G. Yagawa, M. Kikuchi, G. M. Atanasiu, and C. Bratianu, editors, *Proceedings of the International Conference Performance based Engineering for 21st Century*, pages 72–77, Iasi, August 2004. Technical University of Iasi, Romania, Cerni Press.
- [MB04b] A. Muntean and M. Böhm. On a prediction model for the service life of concrete structures based on moving interfaces. In F. Stangenberg, O. T. Bruhns, D. Hartmann, and G. Meschke, editors, *Proceedings of the Second International Conference on Lifetime-Oriented Design Concepts*, pages 209–218, Bochum, March 2004. Ruhr University Bochum, Germany.
- [MBSM01] J. Marchand, D. P. Bentz, E. Samson, and Y. Maltais. Influence of calcium hydroxide dissolution on the transport properties of hydrated cement systems. Technical report, NIST – National Institute of Standards and Technology, 2001.
- [MC99] K. W. Meeks and N. J. Carino. Curing of high-performance concrete: Report of the State-of-the-art. NIST Report 6295, Building and Fire Research Laboratory, Galthersburg, USA, 1999.
- [Mei04] S. A. Meier. Modellierung und Analysis von Diffusions- und Reaktionsprozessen in Medien mit Mikrostruktur. Diplom thesis, Universität Bremen, 2004.
- [MIK03] K. Maekawa, T. Ishida, and T. Kishi. Multi-scale modeling of concrete performance. integrated material and structural mechanics. *Journal of Advanced Concrete Technology*, 1(2):91–126, 2003. Japan Concrete Institute.
- [MPMB05] S. A. Meier, M. A. Peter, A. Muntean, and M. Böhm. Modelling and simulation of concrete carbonation with internal layers. Berichte aus der Technomathematik 05-02, ZeTeM, University of Bremen, 2005.
- [MU01] M. Mainguy and F.-J. Ulm. Coupled diffusion-dissolution around a fracture channel: The solute congestion phenomenon. *Transport in porous media*, 80:481–497, 2001.
- [Mun04] A. Muntean. On the modelling of moisture in concrete-based materials. Unpublished manuscript, 2004.
- [Mun05] A. Muntean. *Moving Carbonation Models*. PhD thesis, ZeTeM, Departement of Mathematics, University of Bremen, 2005. In preparation.
- [NP97] V. T. Ngala and C. L. Page. Effects of carbonation on pore structure and diffusional properties of hydrated cement pastes. *Cement and Concrete Research*, 27(7):995–1007, 1997.
- [Ort94] P. J. Ortoleva. *Geochemical Self-Organization*, volume 23 of *Oxford Monographs on Geology and Geophysics*. Oxford University Press, 1994.

- [Par85] L. J. Parrott. Research on the manufacture and use of cements. In Geoffrey Frohnsdorff, editor, *Proceeding of the Engineering Foundation Conference*, pages 43–73, New Hampshire, 1985.
- [Par90] L. J. Parrott. Assessing carbonation in concrete structures. In J. M. Baker, P. J. Nixon, A. J. Majumdar, and H. Davies, editors, *Durability of building materials and components. Proceedings of the Fifth International Conference held in Brighton*. E. & F. N. Spon, 1990.
- [Par94] L. J. Parrott. Design for avoiding damage due to carbonation – included corrosion. In V. M. Malhotra, editor, *SP-145-15 International Congress on Durability of Concrete*, Nice, CANMET, 1994.
- [Par92] L. J. Parrott. Carbonation, moisture and empty pores. *Advances in Cement Research*, 4(15):111–118, 1991/92.
- [Pet03] M. A. Peter. Modelling and homogenisation of reaction and interfacial exchange in porous media. Diplom thesis, Universität Bremen, 2003.
- [PMMB05] M. A. Peter, A. Muntean, S. A. Meier, and M. Böhm. Modelling and simulation of concrete carbonation: Competitions of several carbonation reactions. Berichte aus der Technomathematik 05-03, ZeTeM, University of Bremen, 2005.
- [PVF89] V. G. Papadakis, C. G. Vayenas, and M. N. Fardis. A reaction engineering approach to the problem of concrete carbonation. *AIChE Journal*, 35:1639, 1989.
- [PVF91] V. G. Papadakis, C. G. Vayenas, and M. N. Fardis. Fundamental modeling and experimental investigation of concrete carbonation. *ACI Materials Journal*, 88(4):363–373, 1991.
- [PVF92] V. G. Papadakis, C. G. Vayenas, and M. N. Fardis. Hydration and carbonation of pozzolanic cements. *ACI Materials Journal*, 89(2):119–130, 1992.
- [SAC03] M. A. Sanjuán, C. Andrade, and M. Cheyrezy. Concrete carbonation tests in natural and accelerated conditions. *Advances in Cement Research*, 15(4):171–180, 2003.
- [Sch76] P. Schießl. Zur Frage der zulässigen Rißbreite und der erforderlichen Betondeckung im Stahlbetonbau unter besonderer Berücksichtigung der Karbonatisierungstiefe des Betons. In *Schriftenreihe des Deutschen Ausschuß für Stahlbetonbau*, volume 255. Berlin, 1976.
- [Sis04] K. Sisomphon. *Influence of pozzolanic material additions on the development of the alkalinity and the carbonation behaviour of composite cement pastes and concretes*. PhD thesis, TU Hamburg-Harburg, 2004.
- [Sis05] K. Sisomphon. Private communications, 2005.
- [SMB99] E. Samson, J. Marchand, and J. J. Beaudoin. Describing ion diffusion in cement-based materials using the homogenization technique. *Cement and Concrete Research*, 29:1341–1345, 1999.
- [SMB05] A. Schmidt, A. Muntean, and M. Böhm. Numerical experiments with self-adaptive finite element simulations in 2D for the carbonation of concrete. Berichte aus der Technomathematik 05-01, ZeTeM, University of Bremen, 2005.
- [SMSB05] E. Samson, J. Marchand, K. A. Snyder, and J. J. Beaudoin. Modeling ion and fluid transport in unsaturated cement systems in isothermal conditions. *Cement and Concrete Research*, 35:141–153, 2005.
- [SON90] T. Saeki, H. Ohga, and S. Nagataki. Change in micro-structure of concrete due to carbonation. *Concrete Library of JSCE*, 420(V-13):1–12, 1990.

- [SSV93] A. V. Saelta, B. A. Schrefler, and R. V. Vitaliani. The carbonation of concrete and the mechanism of moisture, heat and carbon dioxide flow through porous materials. *Cement and Concrete Research*, 23(4):761–772, 1993.
- [SSV95] A. V. Saelta, B. A. Schrefler, and R. V. Vitaliani. 2D model for carbonation and moisture/heat flow in porous materials. *Cement and Concrete Research*, 25(8):1703–1712, 1995.
- [Ste00] A. Steffens. *Modellierung von Karbonatisierung und Chloridbindung zur numerischen Analyse der Korrosionsgefährdung der Betonbewehrung*. PhD thesis, Institute for Statics, Technical University Braunschweig, 2000.
- [SV04] A. V. Saelta and R. V. Vitaliani. Experimental investigation and numerical modeling of carbonation process in reinforced concrete structures. Part I: Theoretical formulation. *Cement and Concrete Research*, 34(4):571–579, 2004.
- [Tay97] H. F. W. Taylor. *Cement Chemistry*. Thomas Telford Publishing, London, 1997.
- [Tor04] J. M. Torrenti. Very long durability of concrete structures: The case of nuclear waste disposal. In F. Stangenberg, O. T. Bruhns, D. Hartmann, and G. Meschke, editors, *Proceedings of the Second International Conference Lifetime-Oriented Design Concepts*, pages 279–286, Bochum, March 2004. Ruhr University Bochum, Germany.
- [Tuu82] K. Tuutti. *Corrosion of steel in concrete*. PhD thesis, Swedish Cement and Concrete Research Institute (CBI), Stockholm, 1982.
- [Ver58] G. J. Verbeck. Carbonation of hydrated portland cement. Technical Report ASTM 205/87, Research and Development Laboratories of the Portland Cement Association, Chicago, 1958.
- [Whi99] S. Whitaker. *The Method of Volume Averaging*. Kluwer Academic Publishers, 1999.
- [Wie84] H.-J. Wierig. Longtime studies on the carbonation of concrete under normal outdoor exposure. In *Proceedings of the RILEM, Hannover University*, pages 239–249. RILEM, 1984.

Reports

Stand: 21. April 2005

- 98–01. Peter Benner, Heike Faßbender:
An Implicitly Restarted Symplectic Lanczos Method for the Symplectic Eigenvalue Problem, Juli 1998.
- 98–02. Heike Faßbender:
Sliding Window Schemes for Discrete Least-Squares Approximation by Trigonometric Polynomials, Juli 1998.
- 98–03. Peter Benner, Maribel Castillo, Enrique S. Quintana-Ortí:
Parallel Partial Stabilizing Algorithms for Large Linear Control Systems, Juli 1998.
- 98–04. Peter Benner:
Computational Methods for Linear–Quadratic Optimization, August 1998.
- 98–05. Peter Benner, Ralph Byers, Enrique S. Quintana-Ortí, Gregorio Quintana-Ortí:
Solving Algebraic Riccati Equations on Parallel Computers Using Newton’s Method with Exact Line Search, August 1998.
- 98–06. Lars Grüne, Fabian Wirth:
On the rate of convergence of infinite horizon discounted optimal value functions, November 1998.
- 98–07. Peter Benner, Volker Mehrmann, Hongguo Xu:
A Note on the Numerical Solution of Complex Hamiltonian and Skew-Hamiltonian Eigenvalue Problems, November 1998.
- 98–08. Eberhard Bänsch, Burkhard Höhn:
Numerical simulation of a silicon floating zone with a free capillary surface, Dezember 1998.
- 99–01. Heike Faßbender:
The Parameterized SR Algorithm for Symplectic (Butterfly) Matrices, Februar 1999.
- 99–02. Heike Faßbender:
Error Analysis of the symplectic Lanczos Method for the symplectic Eigenvalue Problem, März 1999.
- 99–03. Eberhard Bänsch, Alfred Schmidt:
Simulation of dendritic crystal growth with thermal convection, März 1999.
- 99–04. Eberhard Bänsch:
Finite element discretization of the Navier-Stokes equations with a free capillary surface, März 1999.
- 99–05. Peter Benner:
Mathematik in der Berufspraxis, Juli 1999.
- 99–06. Andrew D.B. Paice, Fabian R. Wirth:
Robustness of nonlinear systems and their domains of attraction, August 1999.

- 99–07. Peter Benner, Enrique S. Quintana-Ortí, Gregorio Quintana-Ortí:
Balanced Truncation Model Reduction of Large-Scale Dense Systems on Parallel Computers, September 1999.
- 99–08. Ronald Stöver:
Collocation methods for solving linear differential-algebraic boundary value problems, September 1999.
- 99–09. Huseyin Akcay:
Modelling with Orthonormal Basis Functions, September 1999.
- 99–10. Heike Faßbender, D. Steven Mackey, Niloufer Mackey:
Hamilton and Jacobi come full circle: Jacobi algorithms for structured Hamiltonian eigenproblems, Oktober 1999.
- 99–11. Peter Benner, Vincente Hernández, Antonio Pastor:
On the Kleinman Iteration for Nonstabilizable System, Oktober 1999.
- 99–12. Peter Benner, Heike Faßbender:
A Hybrid Method for the Numerical Solution of Discrete-Time Algebraic Riccati Equations, November 1999.
- 99–13. Peter Benner, Enrique S. Quintana-Ortí, Gregorio Quintana-Ortí:
Numerical Solution of Schur Stable Linear Matrix Equations on Multicomputers, November 1999.
- 99–14. Eberhard Bänsch, Karol Mikula:
Adaptivity in 3D Image Processing, Dezember 1999.
- 00–01. Peter Benner, Volker Mehrmann, Hongguo Xu:
Perturbation Analysis for the Eigenvalue Problem of a Formal Product of Matrices, Januar 2000.
- 00–02. Ziping Huang:
Finite Element Method for Mixed Problems with Penalty, Januar 2000.
- 00–03. Gianfrancesco Martinico:
Recursive mesh refinement in 3D, Februar 2000.
- 00–04. Eberhard Bänsch, Christoph Egbers, Oliver Meincke, Nicoleta Scurtu:
Taylor-Couette System with Asymmetric Boundary Conditions, Februar 2000.
- 00–05. Peter Benner:
Symplectic Balancing of Hamiltonian Matrices, Februar 2000.
- 00–06. Fabio Camilli, Lars Grüne, Fabian Wirth:
A regularization of Zubov's equation for robust domains of attraction, März 2000.
- 00–07. Michael Wolff, Eberhard Bänsch, Michael Böhm, Dominic Davis:
Modellierung der Abkühlung von Stahlbrammen, März 2000.
- 00–08. Stephan Dahlke, Peter Maaß, Gerd Teschke:
Interpolating Scaling Functions with Duals, April 2000.
- 00–09. Jochen Behrens, Fabian Wirth:
A globalization procedure for locally stabilizing controllers, Mai 2000.

- 00–10. Peter Maaß, Gerd Teschke, Werner Willmann, Günter Wollmann:
Detection and Classification of Material Attributes – A Practical Application of Wavelet Analysis, Mai 2000.
- 00–11. Stefan Boschert, Alfred Schmidt, Kunibert G. Siebert, Eberhard Bänsch, Klaus-Werner Benz, Gerhard Dziuk, Thomas Kaiser:
Simulation of Industrial Crystal Growth by the Vertical Bridgman Method, Mai 2000.
- 00–12. Volker Lehmann, Gerd Teschke:
Wavelet Based Methods for Improved Wind Profiler Signal Processing, Mai 2000.
- 00–13. Stephan Dahlke, Peter Maass:
A Note on Interpolating Scaling Functions, August 2000.
- 00–14. Ronny Ramlau, Rolf Clackdoyle, Frédéric Noo, Girish Bal:
Accurate Attenuation Correction in SPECT Imaging using Optimization of Bilinear Functions and Assuming an Unknown Spatially-Varying Attenuation Distribution, September 2000.
- 00–15. Peter Kunkel, Ronald Stöver:
Symmetric collocation methods for linear differential-algebraic boundary value problems, September 2000.
- 00–16. Fabian Wirth:
The generalized spectral radius and extremal norms, Oktober 2000.
- 00–17. Frank Stenger, Ahmad Reza Naghsh-Nilchi, Jenny Niebsch, Ronny Ramlau:
A unified approach to the approximate solution of PDE, November 2000.
- 00–18. Peter Benner, Enrique S. Quintana-Ortí, Gregorio Quintana-Ortí:
Parallel algorithms for model reduction of discrete-time systems, Dezember 2000.
- 00–19. Ronny Ramlau:
A steepest descent algorithm for the global minimization of Tikhonov–Phillips functional, Dezember 2000.
- 01–01. Efficient methods in hyperthermia treatment planning:
Torsten Köhler, Peter Maass, Peter Wust, Martin Seebass, Januar 2001.
- 01–02. Parallel Algorithms for LQ Optimal Control of Discrete-Time Periodic Linear Systems:
Peter Benner, Ralph Byers, Rafael Mayo, Enrique S. Quintana-Ortí, Vicente Hernández, Februar 2001.
- 01–03. Peter Benner, Enrique S. Quintana-Ortí, Gregorio Quintana-Ortí:
Efficient Numerical Algorithms for Balanced Stochastic Truncation, März 2001.
- 01–04. Peter Benner, Maribel Castillo, Enrique S. Quintana-Ortí:
Partial Stabilization of Large-Scale Discrete-Time Linear Control Systems, März 2001.
- 01–05. Stephan Dahlke:
Besov Regularity for Edge Singularities in Polyhedral Domains, Mai 2001.
- 01–06. Fabian Wirth:
A linearization principle for robustness with respect to time-varying perturbations, Mai 2001.

- 01–07. Stephan Dahlke, Wolfgang Dahmen, Karsten Urban:
Adaptive Wavelet Methods for Saddle Point Problems - Optimal Convergence Rates, Juli 2001.
- 01–08. Ronny Ramlau:
Morozov's Discrepancy Principle for Tikhonov regularization of nonlinear operators, Juli 2001.
- 01–09. Michael Wolff:
Einführung des Drucks für die instationären Stokes–Gleichungen mittels der Methode von Kaplan, Juli 2001.
- 01–10. Stephan Dahlke, Peter Maaß, Gerd Teschke:
Reconstruction of Reflectivity Densities by Wavelet Transforms, August 2001.
- 01–11. Stephan Dahlke:
Besov Regularity for the Neumann Problem, August 2001.
- 01–12. Bernard Haasdonk, Mario Ohlberger, Martin Rumpf, Alfred Schmidt, Kunibert G. Siebert:
 h - p -Multiresolution Visualization of Adaptive Finite Element Simulations, Oktober 2001.
- 01–13. Stephan Dahlke, Gabriele Steidl, Gerd Teschke:
Coorbit Spaces and Banach Frames on Homogeneous Spaces with Applications to Analyzing Functions on Spheres, August 2001.
- 02–01. Michael Wolff, Michael Böhm:
Zur Modellierung der Thermoelasto-Plastizität mit Phasenumwandlungen bei Stählen sowie der Umwandlungsplastizität, Februar 2002.
- 02–02. Stephan Dahlke, Peter Maaß:
An Outline of Adaptive Wavelet Galerkin Methods for Tikhonov Regularization of Inverse Parabolic Problems, April 2002.
- 02–03. Alfred Schmidt:
A Multi-Mesh Finite Element Method for Phase Field Simulations, April 2002.
- 02–04. Sergey N. Dachkovski, Michael Böhm:
A Note on Finite Thermoplasticity with Phase Changes, Juli 2002.
- 02–05. Michael Wolff, Michael Böhm:
Phasenumwandlungen und Umwandlungsplastizität bei Stählen im Konzept der Thermoelasto-Plastizität, Juli 2002.
- 02–06. Gerd Teschke:
Construction of Generalized Uncertainty Principles and Wavelets in Anisotropic Sobolev Spaces, August 2002.
- 02–07. Ronny Ramlau:
TIGRA – an iterative algorithm for regularizing nonlinear ill-posed problems, August 2002.
- 02–08. Michael Lukaschewitsch, Peter Maaß, Michael Pidcock:
Tikhonov regularization for Electrical Impedance Tomography on unbounded domains, Oktober 2002.

- 02–09. Volker Dicken, Peter Maaß, Ingo Menz, Jenny Niebsch, Ronny Ramlau:
Inverse Unwuchtidentifikation an Flugtriebwerken mit Quetschöldämpfern, Oktober 2002.
- 02–10. Torsten Köhler, Peter Maaß, Jan Kalden:
Time-series forecasting for total volume data and charge back data, November 2002.
- 02–11. Angelika Bunse-Gerstner:
A Short Introduction to Iterative Methods for Large Linear Systems, November 2002.
- 02–12. Peter Kunkel, Volker Mehrmann, Ronald Stöver:
Symmetric Collocation for Unstructured Nonlinear Differential-Algebraic Equations of Arbitrary Index, November 2002.
- 02–13. Michael Wolff:
Ringvorlesung: Distortion Engineering 2
Kontinuumsmechanische Modellierung des Materialverhaltens von Stahl unter Berücksichtigung von Phasenumwandlungen, Dezember 2002.
- 02–14. Michael Böhm, Martin Hunkel, Alfred Schmidt, Michael Wolff:
Evaluation of various phase-transition models for 100Cr6 for application in commercial FEM programs, Dezember 2002.
- 03–01. Michael Wolff, Michael Böhm, Serguei Dachkovski:
Volumenanteile versus Massenanteile - der Dilatometerversuch aus der Sicht der Kontinuumsmechanik, Januar 2003.
- 03–02. Daniel Kessler, Ricardo H. Nochetto, Alfred Schmidt:
A posteriori error control for the Allen-Cahn Problem: circumventing Gronwall's inequality, März 2003.
- 03–03. Michael Böhm, Jörg Kropp, Adrian Muntean:
On a Prediction Model for Concrete Carbonation based on Moving Interfaces - Interface concentrated Reactions, April 2003.
- 03–04. Michael Böhm, Jörg Kropp, Adrian Muntean:
A Two-Reaction-Zones Moving-Interface Model for Predicting $\text{Ca}(\text{OH})_2$ Carbonation in Concrete, April 2003.
- 03–05. Vladimir L. Kharitonov, Diederich Hinrichsen:
Exponential estimates for time delay systems, May 2003.
- 03–06. Michael Wolff, Michael Böhm, Serguei Dachkovski, Günther Löwisch:
Zur makroskopischen Modellierung von spannungsabhängigem Umwandlungsverhalten und Umwandlungsplastizität bei Stählen und ihrer experimentellen Untersuchung in einfachen Versuchen, Juli 2003.
- 03–07. Serguei Dachkovski, Michael Böhm, Alfred Schmidt, Michael Wolff:
Comparison of several kinetic equations for pearlite transformation in 100Cr6 steel, Juli 2003.
- 03–08. Volker Dicken, Peter Maass, Ingo Menz, Jenny Niebsch, Ronny Ramlau:
Nonlinear Inverse Unbalance Reconstruction in Rotor dynamics, Juli 2003.

- 03–09. Michael Böhm, Serguei Dachkovski, Martin Hunkel, Thomas Lübben, Michael Wolff:
Übersicht über einige makroskopische Modelle für Phasenumwandlungen im Stahl,
Juli 2003.
- 03–10. Michael Wolff, Friedhelm Frerichs, Bettina Suhr:
Vorstudie für einen Bauteilversuch zur Umwandlungsplastizität bei der perlitischen Umwandlung des Stahls 100 Cr6,
August 2003.
- 03–11. Michael Wolff, Bettina Suhr:
Zum Vergleich von Massen- und Volumenanteilen bei der perlitischen Umwandlung der Stähle 100Cr6 und C80,
September 2003.
- 03–12. Rike Grotmaack, Adrian Muntean:
Stabilitätsanalyse eines Moving-Boundary-Modells der beschleunigten Karbonatisierung von Portlandzementen,
September 2003.
- 03–13. Alfred Schmidt, Michael Wolff, Michael Böhm:
Numerische Untersuchungen für ein Modell des Materialverhaltens mit Umwandlungsplastizität und Phasenumwandlungen beim Stahl 100Cr6 (Teil 1),
September 2003.
- 04–01. Liliana Cruz Martin, Gerd Teschke:
A new method to reconstruct radar reflectivities and Doppler information,
Januar 2004.
- 04–02. Ingrid Daubechies, Gerd Teschke:
Wavelet based image decomposition by variational functionals,
Januar 2004.
- 04–03. N. Guglielmi, F. Wirth, M. Zennaro:
Complex polytope extremality results for families of matrices,
März 2004.
- 04–04. I. Daubechies, G. Teschke:
Variational image restoration by means of wavelets: simultaneous decomposition, deblurring and denoising,
April 2004.
- 04–05. V.L. Kharitonov, E. Plischke:
Lyapunov matrices for time-delay systems,
April 2004.
- 04–06. Ronny Ramlau:
On the use of fixed point iterations for the regularization of nonlinear ill-posed problems,
Juni 2004.
- 04–07. Christof Büskens, Matthias Knauer:
Higher Order Real-Time Approximations In Optimal Control of Multibody-Systems For Industrial Robots,
August 2004.

- 04–08. Christof Büskens, Roland Griesse:
Computational Parametric Sensitivity Analysis of Perturbed PDE Optimal Control Problems with State and Control Constraints,
August 2004.
- 04–09. Christof Büskens:
Higher Order Real-Time Approximations of Perturbed Control Constrained PDE Optimal Control Problems ,
August 2004.
- 04–10. Christof Büskens, Matthias Gerdts:
Differentiability of Consistency Functions,
August 2004.
- 04–11. Robert Baier, Christof Büskens, Ilyes Aïssa Chama, Matthias Gerdts:
Approximation of Reachable Sets by Direct Solution Methods of Optimal Control Problems,
August 2004.
- 04–12. J. Soares, G. Teschke, M. Zhariy:
A Wavelet Regularization for Nonlinear Diffusion Equations,
September 2004.
- 05–01. Alfred Schmidt, Adrian Muntean, Michael Böhm:
Numerical experiments with Self-Adaptive Finite Element Simulations in 2D for the Carbonation of Concrete,
April 2005.
- 05–02. Sebastian A. Meier, Malte A. Peter, Adrian Muntean, Michael Böhm:
Modelling and simulation of concrete carbonation with internal layers,
April 2005.
- 05–03. Malte A. Peter, Adrian Muntean, Sebastian A. Meier, Michael Böhm:
Modelling and simulation of concrete carbonation: competition of several carbonation reactions,
April 2005.
- 05–04. Adrian Muntean, Sebastian A. Meier, Malte A. Peter, Michael Böhm, Jörg Kropp:
A note on limitations of the use of accelerated concrete-carbonation tests for service-life predictions,
April 2005.